



**EFFECT OF NaVO_3 CONCENTRATION AND HCl
PRE-TREATMENT ON CORROSION BEHAVIOR
OF ANODIZED COATED AZ91D MAGNESIUM
ALLOYS**

By

KHALID AZADI BIN MAT AKHIR

(1130510717)

A thesis submitted in fulfilment of the requirements for the degree of
Master of Science

**School of Manufacturing Engineering
UNIVERSITI MALAYSIA PERLIS**

2014

THESIS DECLARATION FORM

UNIVERSITI MALAYSIA PERLIS

DECLARATION OF THESIS

Author's full name : KHALID AZADI BIN MAT AKHIR
Date of birth : 10/01/1985
Title : Effect of NaVO₃ Concentration and HCl Pre-Treatment
on Corrosion Behavior of Anodized Coated AZ91D
Magnesium Alloys
Academic Session : _____

I hereby declare that this thesis becomes the property of Universiti Malaysia Perlis (UniMAP) and to be placed at the library of UniMAP. This thesis is classified as:

- CONFIDENTIAL** (Contains confidential information under the Official Secret Act 1972)
- RESTRICTED** (Contains restricted information as specified by the organization where research was done)
- OPEN ACCESS** I agree that my thesis is to be made immediately available as hard copy or on-line open access (full text)

I, the author, give permission to the UniMAP to reproduce this thesis in whole or in part for the purpose of research or academic exchange only (except during a period of _____ years, if so requested above)

Certified by:

SIGNATURE

SIGNATURE OF SUPERVISOR

(NEW IC NO./ PASSPORT NO.)

NAME OF SUPERVISOR

Date : _____

Date: _____

ACKNOWLEDGEMENT

Alhamdulillah, thanks to God Almighty for His bless and strength that He has given to me to finish my research. Even though I faced many challenges during my research that make my research progression become low as well as my motivation. However, thanks to Allah S.W.T and Prophet Muhammad S.A.W, finally I got the strength to move on and capable to finish my research with the support from others.

First of all, most gratitude goes to my supervisor and co-supervisor, En Mohd Zamzuri Mohammad Zain, Dr Mohd Nazree Derman and Siti Norbahiyah binti Mohamad Badari, who providing valuable guidance and suggestions on this work. Their supervisions and support truly help me to keep this research going smoothly and thanks to Cik Siti Norbahiyah Mohamad Badari for her concerned and showing interest in my research and also offering valuable suggestion during various stages of my studies. My special thanks also go to the Dean of School Manufacturing Engineering, Dr Khairul Azwan Ismail for his valuable support.

My grateful thanks also go to the Technical Staff of Universiti Malaysia Perlis at Ulu Pauh Laboratory, En Mazlan, En Jasmin, En Suhelmi and also Technical Staff of Material Laboratory at Taman Muhibbah, En Wan Mohd Arif, who became the backbone of my experimental work. Without their tremendous technical support, I can't manage to complete this project at the time.

I would like to give my sincere appreciations to my research team, Khairiah and Shaza, who has offered their help during my laboratory session. I also acknowledge En Murizam and En Hafiz from School of Material for helping me in using X-Ray Diffraction software (XRD). I would also like to thank a long list of people for many enjoyable scientific discussions and personal conversations – Nurul Farah Wahida Nur Liyana, Ahmad Faizal, Fadzilah, Farah Alina, Puan Kartini, Pn

Marina and every else former and current of Manufacturing group members. Their time, expertise and warm friendship were very much appreciated.

I wish to thank Fundamental Research Grant and My Brain15 by the Ministry of High Education for financially supported during my research work starting from April 2012 until June 2014.

Finally, I want to express my appreciations to my beloved family- Ayah, Mak and not forgetting my wife Siti Nuriyah binti Hamid for their love and encouragement. Thank you very much for supporting me every step of the way.

KHALID AZADI BIN MAT AKHIR
June 2014

© This item is protected by original copyright

TABLE OF CONTENTS

	PAGES
DECLARATION	ii
ACKNOWLEDGEMENT	iii
TABLE OF CONTENTS	v
LIST OF TABLES	viii
LIST OF FIGURES	x
LIST OF ABBREVIATIONS	xviii
LIST OF SYMBOLS	xviii
ABSTRAK	xix
ABSTRACT	xxi
CHAPTER 1 INTRODUCTION	1
1.1 Background	1
1.2 Problem statement	3
1.3 Research objectives	4
1.4 Scope of research	4
1.5 Thesis outline	5
CHAPTER 2 LITERATURE REVIEW	6
2.1 Overview	6
2.2 Magnesium	6
2.2.1 AZ91D Magnesium Alloy	8
2.2.2 Automotive Application	9
2.2.3 Advantages and Disadvantages of AZ91D Magnesium Alloy	11

2.3	Corrosion on Magnesium Alloy	11
2.3.1	Corrosion Reaction on Magnesium Alloy	13
2.4	Coating	15
2.4.1	Anodizing	15
2.4.1.1	Mechanism of Anodizing and Chemical Reaction	16
2.4.1.2	Type of Anodizing	17
2.4.2	Coating Performance Study	18
2.5	Rare Earth Element (REE) Anodizing	22
2.6	Summary	23
CHAPTER 3 METHODOLOGY		24
3.1	Introduction	24
3.2	AZ91D Magnesium Alloy	25
3.3	Sample Preparation	25
3.3.1	Cutting Sample	26
3.3.2	Mounting Sample	26
3.3.3	Polishing Sample	27
3.4	HCl Pre-Treatment	28
3.5	Anodizing coating	28
3.6	Analysis	30
3.6.1	Corrosion test	31
3.6.2	Evaluation Morphologies	32
3.6.3	Electrochemical measurement	33
3.6.4	X-Ray diffraction	34
3.7	Chapter Summary	35
CHAPTER 4 RESULT AND DISCUSSION		36
4.1	Overview	36
4.2	Evaluation of Untreated Sample	37
4.3	Corrosion Behaviour of Untreated Sample	40
4.4	Effect of NaVO ₃ Concentration (Without Pre-Treatment)	42
4.4.1	La (NO ₃) ₃ + Mg (NO ₃) ₂ + NaVO ₃	42
4.4.2	Mg (NO ₃) ₂ + NaVO ₃	46

4.4.3	La (NO ₃) ₃ + NaVO ₃	49
4.5	Corrosion Behaviour of Coating with NaVO ₃ Concentration	53
4.5.1	La (NO ₃) ₃ + Mg (NO ₃) ₂ + NaVO ₃	53
4.5.2	Mg (NO ₃) ₂ + NaVO ₃	59
4.5.3	La (NO ₃) ₃ + NaVO ₃	64
4.6	Summary of Effect of NaVO ₃ Concentration	69
4.7	Effect of HCl Pre-Treatment Before Anodizing Coating	70
4.7.1	La (NO ₃) ₃ + Mg (NO ₃) ₂ + NaVO ₃	70
4.7.2	Mg (NO ₃) ₂ + NaVO ₃	74
4.7.3	La (NO ₃) ₃ + NaVO ₃	78
4.8	Corrosion Behaviour of Sample Coating with HCl Pre-Treatment Before Anodizing Coating	82
4.8.1	La (NO ₃) ₃ + Mg (NO ₃) ₂ + NaVO ₃	82
4.8.2	Mg (NO ₃) ₂ + NaVO ₃	88
4.8.3	La (NO ₃) ₃ + NaVO ₃	93
4.9	Chapter Summary	98
	CHAPTER 5 CONCLUSION AND RECOMMENDATIONS	99
5.1	Conclusion	99
5.2	Recommendation	100
	REFERENCES	101
	APPENDIX A JOURNAL PUBLICATION	103
	APPENDIX B SAMPLE PREPARATION	107
	APPENDIX C ANODIZING PROCESS	109
	APPENDIX D CORROSION TEST PROCESS	110

LIST OF TABLES

NO.		PAGES
1.1	Corrosion potential of commonly used metals and alloys in 3–6% NaCl solutions (ibchem.com, 2003)	2
2.1	List of commonly used magnesium alloys and their compositions (Gupta & Sharon, 2010).	8
2.2	Room temperature mechanical properties of die casting alloys (Gupta & Ling, 2010).	8
2.3	Characteristics and uses of die casting alloys (Gupta & Ling, 2010).	9
2.4	Galvanic Series of Metals and Alloys (Kutz, 2010).	12
2.5	Standard Electrode Potentials in Aqueous Solution at 25°C of some metal (ibchem.com, 2003)	13
3.1	Chemical composition of AZ91D magnesium alloy (wt.%).	25
3.2	The result of the corrosion rate of La (NO ₃) ₃ + Mg (NO ₃) ₂ + NaVO ₃ .	57
3.3	Parameter values of potentiodynamic polarization curves of sample treated in La (NO ₃) ₃ + Mg (NO ₃) ₂ + NaVO ₃	58
3.4	The result of the corrosion rate of Mg (NO ₃) ₂ + NaVO ₃	62
3.5	Parameter values of potentiodynamic polarization curves of sample treated in Mg (NO ₃) ₂ + NaVO ₃	63
3.6	The result of the corrosion rate of La (NO ₃) ₃ + NaVO ₃	67
3.7	Parameter values of potentiodynamic polarization curves of sample treated in La (NO ₃) ₃ + NaVO ₃	68
3.8	The result of the corrosion rate of La (NO ₃) ₃ + Mg (NO ₃) ₂ + NaVO ₃ with various pre-treatment time.	86

3.9	The results of the potentiodynamic corrosion tests in 3.5 wt.% NaCl solution.	87
4.1	The result of the corrosion rate of Mg (NO ₃) ₂ + NaVO ₃ with pre-treatment.	91
4.2	Values of potentiodynamic polarization curves of sample treated in Mg (NO ₃) ₂ + NaVO ₃ with various pre-treatment times.	92
4.3	The result of the corrosion rate pre-treatment with coating in La(NO ₃) ₃ + NaVO ₃	96
4.4	Values of potentiodynamic polarization curves of sample treated in La (NO ₃) ₃ + NaVO ₃ with various pre-treatment times.	97

© This item is protected by original copyright

LIST OF FIGURES

NO.		PAGES
2.1	Specific strength of various structural materials (Gupta & Ling, 2010).	7
2.2	Specific stiffness of various structural materials (Gupta & Ling, 2010).	7
2.3	Automotive components of AZ91D magnesium alloy: (a) rear transfer case made from AZ91D weighing 2.7 kg, and (b) AZ91 magnesium alloy cam cover for Ford Zetec engine weighing 0.9 kg.	10
2.4	Galvanic Corrosion (Song & Guang-Ling, 2011).	14
2.5	Graphical illustration showing the average corrosion rates of AZ91D alloy and AZ91D alloy with Ho additions in 3.5 wt% NaCl solution at 25°C, measured by sample weight loss for 24 h (Gupta & Ling, 2010).	23
3.1	Flow chart methodology of experimental work during evaluation of coating film.	24
3.2	Magnesium alloy.	25
3.3	Flow Chart of Sample Preparation	26
3.4	(a) Magnesium Alloy before Cutting and (b) Magnesium Alloy after Cutting.	26
3.5	(a) Epofix Resin and Epofix Hardener, (b) Mould of sample	27
3.6	Grinding and Polishing machine	28
3.7	Anodizing Diagram	29
3.8	Flow chart methodology of corrosion test.	31

3.9	Optical Microscope at UniMAP's Ulu Pauh Laboratory.	32
3.10	Scanning electron microscope (SEM)UniMAP's Ulu Pauh Laboratory.	33
3.12	Illustration of potentiodynamic polarization curve at UniMAP'S Nano Institute.	34
3.13	XRD machine at School of Bahan UniMAP.	35
4.1	Optical micrograph image of the microstructure of the untreated sample AZ91D magnesium alloy.	37
4.2	SEM backscattered image of the microstructure of the untreated sample AZ91D magnesium alloy.	38
4.3	Polarization curves for the α -phase and the P-phase in 1 M NaCl at pH 11.	39
4.4	XRD patterns of as-cast AZ91D magnesium alloy.	39
4.5	Optical micrographs image of untreated sample after immerse in 5.0% wt NaCl for 72 hours.	40
4.6	SEM image for untreated sample.	41
4.7	Visual inspection for untreated sample after 72 hours immersion test in 3.5% NaCl solutions.	41
4.8	Optical micrograph of Sodium Metavanadate treated formed in electrolytes containing (a) $\text{La}(\text{NO}_3)_3$ and $\text{Mg}(\text{NO}_3)_2$ based solutions and various concentrations Of NaVO_3 , (b) 0.01g/l, (c) 0.05g/l and (d) 0.1g/l respectively.	42

- 4.9 Surface morphology of Sodium Metavanadate treated formed in electrolytes containing (a) $\text{La}(\text{NO}_3)_3$ and $\text{Mg}(\text{NO}_3)_2$ based solutions and various concentrations Of NaVO_3 , (b) 0.01g/l, (c) 0.05g/l and (d) 0.1g/l respectively. 43
- 4.10 Cross section micrographs of AZ91D Mg alloy after anodizing in $\text{Mg}(\text{NO}_3)_2$ and $\text{La}(\text{NO}_3)_3$ with various concentration of NaVO_3 ; (a) 0.01 g/l and (b) 0.05 g/l. 44
- 4.11 XRD patterns for samples treated in $\text{La}(\text{NO}_3)_3 + \text{Mg}(\text{NO}_3)_2$ based solutions with 0.05g/l NaVO_3 as additive. 45
- 4.12 Optical micrograph of Sodium Metavanadate treated formed in electrolytes containing (a) $\text{Mg}(\text{NO}_3)_2$ based solutions and various concentrations of NaVO_3 , (b) 0.01g/l, (c) 0.05g/l and (d) 0.1g/l respectively. 46
- 4.13 Surface morphology of Sodium Metavanadate treated formed in electrolytes containing (a) $\text{Mg}(\text{NO}_3)_2$ based solutions and various concentrations Of NaVO_3 , (b) 0.01g/l, (c) 0.05g/l and (d) 0.1g/l respectively. 47
- 4.14 SEM microstructureCross section of oxide coating AZ91D Mg alloy after anodized in magnesium nitrate $\text{Mg}(\text{NO}_3)_2$ based solutions with differences concentration of NaVO_3 after coating; (a) 0g/l, (b) 0.05g/l 48
- 4.15 Optical micrograph of surface morphology of AZ91D magnesium alloy after coating in $\text{La}(\text{NO}_3)_3$ with NaVO_3 at different concentration (a) 0 g/l, (b) 0.01 g/l; (c) 0.05 g/l; and (d) 0.1g/l respectively. 49

- 4.16 Scanning electron microscopy (SEM) of surface microstructure of AZ91D magnesium alloy after coating those anodized in $\text{La}(\text{NO}_3)_3$ based solution with NaVO_3 at different concentration respectively: (a) 0 g/l; (b) 0.01 g/l; (c) 0.05 g/l; and (d) 0.1g/l. 50
- 4.17 SEM microstructure cross section of oxide coating AZ91D Mg alloy after anodized in $\text{La}(\text{NO}_3)_3$ based solutions with differences concentration of NaVO_3 after coating respectively; (a) 0.01g/l, (b) 0.1g/l 51
- 4.18 XRD patterns for samples treated in $\text{La}(\text{NO}_3)_3$ based solutions with 0.1g/l NaVO_3 as additive. 52
- 4.19 Optical micrograph of surface morphology of AZ91D magnesium alloy after 72hours of corrosion test in 3.5% NaCl solution those anodized in $\text{La}(\text{NO}_3)_3 + \text{Mg}(\text{NO}_3)_2$ with NaVO_3 at different concentration respectively: (a) 0 g/l; (b) 0.01 g/l; (c) 0.05 g/l; and (d) 0.1g/l 53
- 4.20 SEM of surface morphology of AZ91D magnesium alloy after 72hours of corrosion test in 3.5% NaCl solution those anodized in $\text{La}(\text{NO}_3)_3 + \text{Mg}(\text{NO}_3)_2$ with NaVO_3 at different concentration respectively: (a) 0 g/l; (b) 0.01 g/l; (c) 0.05 g/l; and (d) 0.1g/l 55
- 4.21 Corrosion rate of AZ91D Magnesium Alloy and different anodizing coatings after immersed in 3.5% NaCl solution for 72 hours. 56
- 4.22 Potentiodynamic polarization curves of untreated and treated sample in anodized with different concentration of NaVO_3 in 3.5 wt% NaCl solution. 57

- 4.23 Optical micrograph of surface morphology of AZ91D magnesium alloy after 72 hours of corrosion test in 3.5% NaCl solution those (a) anodized in $\text{Mg}(\text{NO}_3)_2$ based solution, with different concentration NaVO_3 (b) 0.01 g/l; (c) 0.05g/l and (d) 0.1g/l respectively. 59
- 4.24 SEM of surface morphology of AZ91D magnesium alloy after 72 hours of corrosion test in 3.5% NaCl solution those (a) anodized in $\text{Mg}(\text{NO}_3)_2$ based solution, with different concentration NaVO_3 (b) 0.01 g/l; (c) 0.05g/l and (d) 0.1g/l respectively. 60
- 4.25 Corrosion rate of AZ91D Magnesium Alloy and different anodizing coatings after immersed in 3.5% NaCl solution for 72 hours. 61
- 4.26 Potentiodynamic polarization curves of untreated and treated sample those anodized in $\text{Mg}(\text{NO}_3)_2$ with different concentration of NaVO_3 in 3.5 wt% NaCl solution. 62
- 4.27 Optical micrograph of surface morphology of AZ91D magnesium alloy after 72 hours of corrosion test in 3.5% NaCl solution those anodized in $\text{La}(\text{NO}_3)_3$ with NaVO_3 at different concentration respectively: (b) 0.01 g/l; (c) 0.05 g/l; and (d) 0.1g/l . 64
- 4.28 SEM of surface morphology of AZ91D magnesium alloy after 72 hours of corrosion test in 3.5% NaCl solution those anodized in $\text{La}(\text{NO}_3)_3$ with NaVO_3 at different concentration respectively: (a) 0 g/l; (b) 0.01 g/l; (c) 0.05 g/l; and (d) 0.1g/l 65

4.29	Corrosion rate of AZ91D Magnesium Alloy and different anodizing coatings after immersed in 3.5% NaCl solution for 72 hours.	66
4.30	Potentiodynamic polarization curves of untreated and treated sample in anodized with different concentration of NaVO ₃ in 3.5 wt% NaCl solution.	67
4.31	Optical micrograph of Sodium Metavanadate treated formed in solution containing La(NO ₃) ₃ , Mg(NO ₃) ₂ and NaVO ₃ with HCl pre-treatment time (a) 15sec, (b) 20sec (c) 25sec and (d) 30sec respectively	70
4.32	Surface morphologies of AZ91D Mg alloy, those anodized in La(NO ₃) ₃ +Mg (NO ₃) ₂ + NaVO ₃ solution with varies pre-treatment time of (a) 15s, (b) 20s (c) 25s and (d) 30s respectively	71
4.33	Cross-sectional morphologies with vanadium treated at different pre-treatment time of (a) 20s and (b) 25s respectively	72
4.34	XRD graph for sample 20s pre-treatment time, those coated in La(NO ₃) ₃ + Mg(NO ₃) ₂ + NaVO ₃ solution.	73
4.35	Surface micrographs for AZ91D Mg alloy those anodized in Mg(NO ₃) ₂ + NaVO ₃ solution with pre-treatment time of (a) 15s (b) 20s (c) 25s and (d) 30s respectively.	74
4.36	Surface morphologies of AZ91D Mg alloy, those anodized in Mg(NO ₃) ₂ + NaVO ₃ solution with varies pre-treatment time of (a) 15s (b) 20s (c) 25s (d) 30s respectively.	75

4.37	Cross-sectional morphologies coating with $\text{Mg}(\text{NO}_3)_2$ and NaVO_3 treated at different pre-treatment time of (a) 20s and (b) 25s respectively.	76
4.38	XRD graph for sample 25s of pre-treatment time, those coated in $\text{Mg}(\text{NO}_3)_2 + \text{NaVO}_3$ solution.	77
4.39	Surface micrographs for AZ91D Mg alloy those anodized in $\text{La}(\text{NO}_3)_3 + \text{NaVO}_3$ solution with varies pre-treatment time of (a) 15s (b) 20s (c) 25s and (d) 30s respectively	78
4.40	Surface morphologies of AZ91D Mg alloy, those anodized in $\text{La}(\text{NO}_3)_3 + \text{NaVO}_3$ solution with varies pre-treatment time of (a) 15s (b) 20s (c) 25s (d) 30s respectively	79
4.41	Cross-sectional morphologies coating with $\text{La}(\text{NO}_3)_3$ and NaVO_3 treated at different pre-treatment time of (a) 20s and (b) 30s respectively.	80
4.42	XRD graph for sample 20s of pre-treatment time, those coated in $\text{La}(\text{NO}_3)_3 + \text{NaVO}_3$ solution.	81
4.43	Surface micrographs for AZ91D Mg alloy after corrosion test, those anodized in $\text{La}(\text{NO}_3)_3 + \text{Mg}(\text{NO}_3)_2 + \text{NaVO}_3$ solution with pre-treatment time of (a) 15s, (b) 20s (c) 25s (d) 30s respectively.	82
4.44	Surface morphologies of AZ91D Mg alloy after corrosion test those anodized in $\text{La}(\text{NO}_3)_3 + \text{Mg}(\text{NO}_3)_2 + \text{NaVO}_3$ solution with (a) 15s, (b) 20s, (c) 25s, and (d) 30s pre-treatment respectively	84
4.45	Result of anti-corrosion test of AZ91D magnesium alloy after coating with $\text{La}(\text{NO}_3)_3 + \text{Mg}(\text{NO}_3)_2 + \text{NaVO}_3$ solution.	85

4.46	Polarization graph for AZ91D Mg alloy those anodized in $\text{La}(\text{NO}_3)_3 + \text{Mg}(\text{NO}_3)_2 + \text{NaVO}_3$ solution with varies pre-treatment time of (a) 20s, (b) 25s, and (c) untreated respectively.	86
4.47	Surface micrographs for AZ91D Mg alloy, those anodized in $\text{Mg}(\text{NO}_3)_2 + \text{NaVO}_3$ solution with pre-treatment time of (a) 15s, (b) 20s, (c) 25s, (d) 30s, after corrosion respectively	88
4.48	Surface morphologies of AZ91D Mg alloy, those anodized in $\text{Mg}(\text{NO}_3)_2 + \text{NaVO}_3$ solutions with pre-treatment time of (a) 15s, (b) 20s, (c) 25s and (d) 30s after corrosion respectively	89
4.49	Result of corrosion rate of AZ91D magnesium alloy after coating with $\text{Mg}(\text{NO}_3)_2 + \text{NaVO}_3$ solutions.	90
4.50	Polarization graph for AZ91D Mg alloy those anodized in $\text{Mg}(\text{NO}_3)_2 + \text{NaVO}_3$ solution with varies pre-treatment times.	91
4.51	Surface micrographs for AZ91D Mg alloy, those anodized in $\text{La}(\text{NO}_3)_3 + \text{NaVO}_3$ solution with pre-treatment time of (a) 15s, (b) 20s (c) 25s (d) 30s, after corrosion respectively	93
4.52	Surface morphologies of AZ91D Mg alloy, those anodized in $\text{La}(\text{NO}_3)_3 + \text{NaVO}_3$ solution with pre-treatment time of (a) 15s, (b) 20s, (c) 25s and (d) 30s after corrosion respectively.	94
4.53	Result of corrosion rate of AZ91D magnesium alloy after pre-treatment and coating with $\text{La}(\text{NO}_3)_3 + \text{NaVO}_3$ solutions	95
4.54	Polarization graph for AZ91D Mg alloy those anodized in $\text{La}(\text{NO}_3)_3 + \text{NaVO}_3$ solution with varies pre-treatment time of 15s, 20s and untreated.	96

LIST OF ABBREVIATIONS

EDX	Energy Dispersive X-Ray
Hr	Hour
La	Lanthanum
MAO	Micro-arc oxidation
Mg	Magnesium
MgO	Magnesium Oxide
Mg(OH) ₂	Magnesium Hydroxide
NaCl	Sodium Chloride
NaVO ₃	Sodium Metavanadate
PEO	Plasma Electrolytic Oxidation
SEM	Scanning Electron Microscope
V	Vanadium
V ₂ O ₅	Vanadium Oxide
XRD	X-ray Diffraction

LIST OF SYMBOLS

α	Alpha Phase
β	Beta Phase
A/cm ²	Current Density
R _p	Resistance polarization
Cr	Corrosion Rate
mm/y	Millimetre per year
V	Voltage

**KESAN KEPEKATAN NaVO_3 DAN HCl PRA-RAWATAN KE ATAS SIFAT
PENGARATAN BAGI SALUTAN ANODIZING KE ATAS AZ91D
MAGNESIUM ALOI.**

ABSTRAK

Magnesium dan magnesium aloi mempunyai beberapa ciri yang sangat baik seperti ketumpatan paling rendah dalam logam industri, nisbah kekuatan kepada berat yang tinggi, penyerapan gegaran dan elektromagnet ciri-ciri perisai gelombang. Oleh kerana sifat-sifat ini, magnesium dan magnesium aloi boleh digunakan dalam pembuatan komponen untuk kenderaan bermotor, barangan elektronik dan dalam pembuatan barangan sukan. Di samping itu, magnesium dan magnesium aloi lebih mudah dikitar semula daripada resin sintetik, sekaligus menjadikan ia sebagai bahan mesra alam. Rintangan yang rendah terhadap kakisan ataupun pengaratan telah menghadkan penggunaan magnesium dan magnesium aloi di dalam perindustrian. Salutan anodizing adalah salah satu teknik yang kos rendah, efektif dan mudah untuk digunakan bagi menghasilkan lapisan logam ke atas substrat. Kajian ini berkaitan dengan penyediaan filem oksida ke atas permukaan AZ91D magnesium aloi oleh salutan anodizing dan HCl pra-rawatan sebelum anodizing dalam larutan yang mengandungi $\text{La}(\text{NO}_3)_3$ dan / atau $\text{Mg}(\text{NO}_3)_2$, dengan penambahan kepekatan NaVO_3 dalam larutan. Lapisan anodizing telah dihasilkan pada permukaan AZ91D magnesium aloi dan kesan kepekatan NaVO_3 dan HCl pra rawatan telah dikaji. Satu sebatian kimia AlO , MgO dan VO dikesan dari puncak corak XRD bagi mengesahkan pembentukan lapisan oksida pada permukaan AZ91D magnesium aloi. Rintangan kakisan AZ91D magnesium aloi telah meningkat dengan mendadak dengan kadar kakisan 0.2 mm/y telah diperolehi. Morfologi penyembuhan diri boleh

diperhatikan daripada SEM imej menunjukkan pemulihan bagi NaVO_3 yang kaya dengan oksida dari penyelesaian NaCl yang teruk. Keputusan yang baik bagi setiap larutan ini dikekalkan untuk penambahbaikan oleh HCl pra-rawatan. Satu permukaan kasar telah diperolehi selepas merendam dalam larutan HCl selama 20s dan diikuti dengan proses anodizing, telah menghasilkan kadar kakisan sehingga 0.19 mm/y. Dua puncak yang dikesan telah mengandungi sebatian kimia VO dan MgO dikesan dari corak XRD. Perlindungan kakisan AZ91D magnesium aloi telah meningkat dengan cara-cara berikut; pembentukan morfologi penyembuhan diri untuk pulih daripada alam sekitar yang teruk dengan penambahan NaVO_3 dan pembentukan lapisan oksida yang pasif pada permukaan AZ91D aloi magnesium oleh rendaman dalam larutan HCl . Berdasarkan eksperimen elektrokimia potentiodynamics polarisasi dan keputusan ujian rendaman, larutan yang mengandungi NaVO_3 dan HCl pra-rawatan berjaya meningkatkan rintangan kakisan pada AZ91D aloi magnesium. Hasil kukuh yang ditunjukkan di sini akan menyumbang kepada permintaan yang luas kepada magnesium aloi dalam bidang industri automotif.

**EFFECT OF NaVO_3 CONCENTRATION AND HCL PRE-TREATMENT ON
CORROSION BEHAVIOR OF ANODIZED COATED AZ91D MAGNESIUM
ALLOYS**

ABSTRACT

Magnesium and its alloys have some excellent properties, such as the lowest density of industrial metals, a high strength-to-weight ratio, vibration absorbency and electromagnetic wave shield characteristics. Because of these properties, magnesium and its alloys can be applied in the manufacture of components for motor vehicles, in housing for electronics, and in the manufacture of sporting goods. In addition, magnesium and its alloys are more easily recycled than synthetic resins, which make these materials eco-friendly. The poor resistance of magnesium and its alloys to corrosion has limited the application of these materials in corrosive environments. Anodizing coating is one of the most cost effective and simple techniques for introducing a metallic coating to a substrate. This study deals with the preparation of oxide films on AZ91D magnesium alloy by anodizing coating in a solution containing $\text{La}(\text{NO}_3)_3$ and/or $\text{Mg}(\text{NO}_3)_2$, with additive NaVO_3 concentration in the solution. The anodizing coating on the AZ91D magnesium alloy has been carried out and the effect of NaVO_3 concentrations and pre-treatment was investigated. A chemical compound of AlO, MgO and VO was detected from the diffraction peaks of XRD pattern confirming the formation of an oxide layer on the surface of AZ91D magnesium alloy. The corrosion resistance of AZ91D magnesium alloy increases remarkably with corrosion rate of 0.2 mm/y was obtained. A self-healing morphology could be observed from SEM images indicated the recovery of the NaVO_3 rich oxide film from the severe environment of NaCl solution. This result is

remained constant for further improvement by HCl pre-treatment. A rough surface was obtained after immersing in HCl solution for 20 s and followed by anodizing, has yielded the corrosion rate up to 0.19 mm/y. Two peaks assigned for VO and MgO was detected from XRD patterns. The corrosion protection of AZ91D magnesium alloy has been increased by the following ways; the formation of self-healing morphology to recover from the severe environment by the addition of NaVO₃, and formation of a passive oxide layer on the surface of AZ91D magnesium alloy by immersion in HCl solution. Based on the electrochemical experiments of potentiodynamics polarization and immersion test result, coating with NaVO₃ and HCl pre-treatment successfully increased the corrosion resistance of AZ91D magnesium alloy. The result demonstrated here will strongly contribute to the broad application of magnesium alloy in the field of the automotive industry.

CHAPTER 1

INTRODUCTION

1.1 Background

Economic pressure causes the nation to struggle in minimizing the fuel consumption. Due to that issue, utilizing the lightweight material in automotive industries becomes a prominence solution in reducing the fuel consumption, hence the emission of pollutants. Automotive industry has select aluminium which is a low density (2.7 g/cm^3) as compared to other metals as the main material in their vehicle parts production. However, the widespread use of aluminium has leads to the shortage of the source, thus indirectly cause the aluminium to become an expensive metal. A lot of researchers had study on other alternative materials that suits automotive applications. Magnesium is the best alternative solution to reduce the weight of each component in automotive. Magnesium alloy is a promising engineering material due to the properties of low density about 1.74g/cm^3 with high specific strength compared to other common material used in automotive such as iron, ferrous, etc. (Cheong, 2006). However, the low corrosion resistance of magnesium has limited its application. To overcome this problem, many researchers have studied to develop an advanced coating to reduce the corrosion and wear resistant of magnesium.

Magnesium, magnesium alloys, and magnesium composites are strong candidates for the existing and emerging engineering applications due to their low

density and high strength to weight ratio. In a dry atmospheric condition magnesium-based materials are quite stable from corrosion perspective due to the reasonably protective nature of their oxide. However, in aqueous environment, magnesium is anodic to most other metals due to its strongly negative electrode potential (Table 1.1). Owing to its poor corrosion properties, magnesium-based materials are prone to galvanic corrosion, which can result in severe pitting. Thus, this will reduce the mechanical performance and greatly limits the usage of magnesium-based materials (Gupta & Ling, 2010).

Table 1.1: Corrosion potential of commonly used metals and alloys in 3–6% NaCl solutions (ibchem.com, 2003)

Metal or Alloy	Corrosion Potential (V)
Mg	-1.73
Mg alloys	-1.67
Zn	-1.05
Al (99.99%)	-0.85
Mild steel	-0.78
Cast iron	-0.73

It is well known that magnesium (Mg) alloys are not corrosion resistant and require surface treatments or coatings in many applications. A variety of surface finishing processes are being used to protect magnesium alloys from corrosion, which include Electrochemical Coating (MAO, Nickel Composite Coating, Anodizing), Gas Phase Deposition (CVD & PVD), Thermal Spray Coating etc. These coating techniques should be considered to enhance a protective surface treatment becomes an essential part of the manufacturing process for magnesium components that are to be used in humid or corrosive environments.