



**PHYSICAL AND MECHANICAL STUDIES OF  
KAOLIN-BASED GEOPOLYMER MASONRY  
BRICK**

by

**MUHAMMAD FAHEEM BIN MOHD TAHIR  
(1230410777)**

A thesis submitted in fulfillment of the requirements for the degree of  
Master of Science in Materials Engineering

**School of Materials Engineering  
UNIVERSITI MALAYSIA PERLIS  
2015**

# UNIVERSITI MALAYSIA PERLIS

## DECLARATION OF THESIS

Author's full name : MUHAMMAD FAHEEM BIN MOHD TAHIR  
Date of birth : 24 AUGUST 1987  
Title : PHYSICAL AND MECHANICAL STUDY OF KAOLIN-BASED  
GEOPOLYMER MASONRY BRICK  
Academic Session : 2014/2015

I hereby declare that this thesis becomes the property of Universiti Malaysia Perlis (UniMAP) and to be placed at the library of UniMAP. This thesis is classified as :

**CONFIDENTIAL** (Contains confidential information under the Official Secret Act 1972)\*

**RESTRICTED** (Contains restricted information as specified by the organization where research was done)\*

**OPEN ACCESS** I agree that my thesis is to be made immediately available as hard copy or on-line open access (full text)

I, the author, give permission to the UniMAP to reproduce this thesis in whole or in part for the purpose of research or academic exchange only (except during a period of \_\_\_\_ years, if so requested above).

Certified by:

\_\_\_\_\_  
**SIGNATURE**

870824-43-5007

\_\_\_\_\_  
**SIGNATURE OF SUPERVISOR**

BRIG.JEN. DATUK PROF.EMERITUS DR. KAMARUDIN HUSIN

(NEW IC NO. / PASSPORT NO.)

**NAME OF SUPERVISOR**

Date: \_\_\_\_\_

Date: \_\_\_\_\_

**NOTES:**\* If the thesis is CONFIDENTIAL or RESTRICTED, please attach with the letter from the organization with period and reasons for confidentiality or restriction.

## AKNOWLEDGEMENT

*All praise to Allah, the Lord of the Universe*

Firstly, thanks to Allah, the Most Gracious Most Merciful because I finally accomplish my research on Master Degree in Materials Engineering. My special gratitude and appreciation goes to my project supervisor, Brig. Jen. Datuk Professor Emeritus Dr. Kamarudin Hussin and both my co-supervisor, Associate Professor Dr. Che Mohd Ruzaidi Ghazali and Associate Professor Dr. Mohd Mustafa Al Bakri Abdullah for their encouragement, continuous guidance, endless patience, and valuable with the blend of fruitful advice throughout the period of study. I also would like to thank both examiner, Associate Professor Dr. Aeslina Abdul Kadir and Dr. Azlin Fazlina Osman for their guidance and advice.

My gratitude is also extended to Mr. Mohd Nasir Ibrahim, Mr. Azmi Aziz and Mr. Mohamad Safwan Isa, technician and lecturer of School of Materials Engineering, UniMAP, for assisting in putting my research study into action and for their help and guidance during laboratory works. I also indebted to Center of Excellence Geopolymer & Green Technology (CEGeoGTech) for providing the facilities for my study and research.

I would like to express my gratitude to my mother Hajah Rohani Ahmad, my father Haji Mohd Tahir Mohd Arshad, my wife Shahidah Arina Shamsuddin and my beloved family who always very supportive and encouraging towards accomplishment of my research.

Lastly, I would like to extend my appreciation to my fellow CEGeoGTech researcher and to those who have helped directly or indirectly, thanks for everything.

## TABLE OF CONTENTS

	<b>PAGES</b>
<b>THESIS DECLARATION</b>	i
<b>ACKNOWLEDGEMENT</b>	ii
<b>TABLE OF CONTENTS</b>	iii
<b>LIST OF FIGURES</b>	vii
<b>LIST OF TABLES</b>	xi
<b>LIST OF ABBREVIATIONS</b>	xii
<b>ABSTRAK</b>	xiv
<b>ABSTRACT</b>	xv
<b>CHAPTER 1 INTRODUCTION</b>	
1.1 Background	1
1.2 Problem Statement	3
1.3 Objectives of Study	5
1.4 Scope of Research	5
1.5 Organization of Thesis	6
<b>CHAPTER 2 LITERATURE REVIEW</b>	
2.1 Introduction	8
2.2 Definition of Brick	8
2.3 Type of Bricks	9
2.3.1 Clay Brick	9
2.3.2 Concrete Masonry Brick	10
2.3.3 Calcium-Silicate Brick	12
2.4 Size of Brick	13
2.5 Classification of Brick	14
2.5.1 Building Bricks	14
2.4.2 Facing Bricks	15

2.5.3 Engineering Bricks	16
2.6 Introduction to Geopolymer	16
2.6.1 Geopolymerization	19
2.7 Geopolymer in Brick Production	23
2.8 Materials to Produce Kaolin - Based Geopolymer Brick	28
2.8.1 Kaolin	28
2.8.2 Aggregates	31
2.8.3 Alkaline Activator	31
2.9 Engineering Properties of Brick	34
2.9.1 Compressive Strength	34
2.9.2 Density	35
2.9.3 Water Absorption	36
2.9.4 Durability	36
2.10 Conclusion	37

### **CHAPTER 3 RESEARCH METHODOLOGY**

3.1 Introduction	38
3.2 Materials	40
3.3.1 Kaolin	40
3.3.2 Alkaline Activator	41
3.3.3 Fine Aggregate (Quarry Dust)	43
3.4 Preparation of Kaolin - Based Geopolymer Brick	43
3.4.1 Preparation of NaOH Solution	45
3.4.2 Preparation of Alkaline Activator Solution	46
3.4.3 Mixing Process	46
3.4.4 Moulding and Compaction Process	48
3.4.5 Curing Process	49
3.5 Mix Design	50
3.5.1 Detail of Mixture Proportion	51
3.5.1.1 Effect of Kaolin/Alkaline Activator ratio	51
3.5.1.1 Effect of $\text{Na}_2\text{SiO}_3/\text{NaOH}$ ratio	52
3.5.1.1 Effect of Sand/Kaolin ratio	53

3.6 Testing Procedure	54
3.6.1 Compressive Strength Test	54
3.6.2 Water Absorption Test	55
3.6.3 Density Analysis	56
3.6.4 Dimension Test	57
3.6.5 Morphology Analysis	61

## **CHAPTER 4 RESULTS AND DISCUSSION**

4.1 Introduction	62
4.2 Raw Materials Characterization	63
4.2.1 Chemical Composition Analysis	63
4.2.2 Microstructure Analysis	64
4.2.3 Elemental Analysis	66
4.2.4 Phase Analysis	68
4.2.5 Chemical Bonding Analysis	69
4.3 Effect of Different Kaolin to Alkaline Activator Ratios	70
4.3.1 Density	71
4.3.2 Water Absorption	72
4.3.3 Compressive Strength	73
4.4 Effect of Different $\text{Na}_2\text{SiO}_3$ to NaOH Ratios	74
4.4.1 Density	75
4.4.2 Water Absorption	76
4.4.3 Compressive Strength	77
4.5 Effect of Different Sand to Kaolin Ratios	78
4.5.1 Density	78
4.5.2 Water Absorption	79
4.5.3 Compressive Strength	80
4.6 Correlation (r value)	81
4.6.1 Correlation for Different Kaolin to Alkaline Activator Ratios	82
4.6.2 Correlation for Different $\text{Na}_2\text{SiO}_3$ to NaOH Ratios	84
4.6.3 Correlation for Different Sand to Kaolin Ratios	86
4.7 Dimensional Tolerances	86

4.7 Structure Analysis of Kaolin - Based Geopolymer Bricks	87
4.7.1 Phase Analysis	87
<b>CHAPTER 5 CONCLUSIONS AND RECOMMENDATIONS</b>	
5.1 Introduction	93
5.1.1 Production of Kaolin - Based Geopolymer Bricks	93
5.1.2 Physical and Mechanical Properties of Kaolin - Based Geopolymer Bricks	94
5.1.3 Relationship between Compressive Strength, Density and Water Absorption of Kaolin - Based Geopolymer Bricks	95
5.2 Recommendations	95
REFERENCES	97
APPENDIX A	103
APPENDIX B	105
LIST OF PUBLICATIONS	119

## LIST OF FIGURES

NO.		PAGE
2.1	The difference between working and coordinating size(Civil Engineering Terms, 2011)	10
2.2	Clay bricks	10
2.3	Concrete bricks	12
2.4	Calcium silicate bricks	13
2.5	Schematic outline of the reaction processes involved in geopolymerisation (Van Deventer, et. al., 2007)	21
2.6	Structure of kaolinite (Varga, 2007)	29
2.7	SEM micrographs of kaolinite (Varga, 2007)	29
3.1	Sequences of research laboratory work	39
3.2	Sodium hydroxide (NaOH)	42
3.3	Sodium silicate ( $\text{Na}_2\text{SiO}_3$ ) solutions	43
3.4	Geopolymer Brick Production Machine	45
3.5	Schematic Diagram of Mixing Process Part in Geopolymer Brick Production Machine	47
3.6	Mixing Sequence	47
3.7	Schematic Diagram of Moulding and Compaction Process Part in Geopolymer Brick Production Machine	48
3.8	Curing Chamber	49
3.9	Curing process by using oven	50
3.10	Arrangement to measure the length of a 24 unit bricks	58
3.11	Arrangement to measure the height of a 24 unit bricks	59
3.12	Arrangement to measure the width of a 24 unit bricks	60
4.1	SEM micrograph of kaolin at magnification 2000	65



4.2	SEM micrograph of kaolin at magnification 5000	66
4.3	EDX spectrum of kaolin	67
4.4	XRD diffractogram of kaolin (K - Kaolinite; Q - Quartz; D - dickite; A - Alunite)	68
4.5	FTIR spectrum of kaolin.	69
4.6	Density of kaolin – based geopolymer brick with different kaolin-to-alkaline activator	71
4.7	Percentage of water absorption of kaolin – based geopolymer brick with different kaolin-to-alkaline activator	72
4.8	Compressive strength of kaolin – based geopolymer brick with different kaolin-to-alkaline activator	73
4.9	Density of kaolin – based geopolymer brick with different Na <sub>2</sub> SiO <sub>3</sub> to NaOH Ratios	75
4.10	Percentage of water absorption of kaolin – based geopolymer brick with different Na <sub>2</sub> SiO <sub>3</sub> to NaOH Ratios	76
4.11	Compressive strength of kaolin – based geopolymer brick with different Na <sub>2</sub> SiO <sub>3</sub> to NaOH Ratios	77
4.12	Density of kaolin – based geopolymer brick with different Sand to Kaolin Ratios	79
4.13	Percentage of water absorption of kaolin – based geopolymer brick with different Sand to Kaolin Ratios	80
4.14	Compressive strength of kaolin - based geopolymer brick with different Sand to Kaolin Ratios	81
4.15	Correlation between density and compressive strength of kaolin - based geopolymer brick with different kaolin to alkaline activator ratios	82
4.16	Correlation between density and water absorption of kaolin - based geopolymer brick with different kaolin to alkaline activator ratios	83
4.17	Correlation between compressive strength and water absorption of kaolin - based geopolymer brick with different kaolin to alkaline activator ratios	83
4.18	Correlation between density and compressive strength of kaolin - based geopolymer brick with different Na <sub>2</sub> SiO <sub>3</sub> to NaOH ratios	84

4.19	Correlation between density and water absorption of kaolin - based geopolymer brick with different Na <sub>2</sub> SiO <sub>3</sub> to NaOH ratios	85
4.20	Correlation between compressive strength and water absorption of kaolin - based geopolymer brick with different Na <sub>2</sub> SiO <sub>3</sub> to NaOH ratios	85
4.21	XRD analysis of kaolin - based geopolymer brick with different ratios of kaolin to alkaline activator.	89
4.22	XRD analysis of kaolin - based geopolymer brick with different ratios of Na <sub>2</sub> SiO <sub>3</sub> to NaOH.	90
4.23	XRD analysis of kaolin - based geopolymer brick with different ratios of Sand to Kaolin.	91
4.23	XRD analysis of raw kaolin with kaolin - based geopolymer brick	92

©This item is protected by original copyright

## LIST OF TABLES

NO.		PAGE
2.1	Strength, absorption and density classification of concrete building bricks (ASTM C55, 2011)	11
2.2	Classes of Calcium Silicate Bricks (BS 187: 1978)	13
2.3	Sizes of Bricks (BS 3921: 1985)	14
2.4	Classification of Bricks by Compressive Strength and Water Absorption (BS 3921: 1985)	16
2.5	Applications of Geopolymer Material (Davidovits, 1999)	19
2.6	Alkaline Activator, Curing Condition and Compressive Strength for Various Types of Geopolymer Bricks	27
2.7	Density, Water Absorption and Compressive Strength for Various Types of Masonry Bricks	35
2.8	Density Classification Requirement for Non-Loadbearing Masonry Units (ASTM C129, 2011)	36
3.1	Properties of kaolin	40
3.2	Specification of $\text{Na}_2\text{SiO}_3$	41
3.3	Information of NaOH	42
3.4	Size of bricks (BS 3921, 1985)	44
3.5	General Calculation of Mixtures.	51
3.6	Detail of mixture proportions with different Kaolin to Activator ratio	52
3.7	Detail of mixture proportions with different $\text{Na}_2\text{SiO}_3$ to NaOH ratio.	53
3.8	Detail of mixture proportions with different Sand to Kaolin ratio.	54
3.9	Allowable dimensional deviations recommended by BS 3921 (1985)	57
4.1	Oxide composition of kaolin and sand obtained by XRF analysis	63

4.2	Mass percentage of elements in kaolin	67
4.3	Assignments of FTIR absorption bands in kaolin.	70
4.4	Dimensions of bricks measured	86

©This item is protected by original copyright

## LIST OF ABBREVIATIONS

ASTM	- American Society for Testing and Materials
Si	- Silica
Al	- Alumina
O	- Oxygen
XRD	- X-Ray Diffraction
SEM	- Scanning Electron Microscopy
BS	- British Standard
FBS	- Face Brick Standard
FBX	- Face Brick Extra
FBA	- Face Brick Aesthetic
Fe	- Iron
Ti	- Titanium
P	- Phosphorus
S	- Sulfur
Mg	- Magnesium
K	- Potassium
Ca	- Calcium
Zn	- Zinc
Sr	- Strontium
XRF	- X-Ray Fluorescence
CaO	- Calcium Oxide
NaOH	- Sodium Hydroxide
Na <sub>2</sub> SiO <sub>3</sub>	- Sodium Silicate

MPa	- Mega Pascal
EPA	- Environmental Protection Agency
TCLP	- Toxicity Characteristic Leaching Procedure
CO <sub>2</sub>	- Carbon Dioxide
SiO <sub>4</sub>	- Silicate
AlO <sub>4</sub>	- Aluminates
OPC	- Ordinary Portland Cement
CEGeoGTech	- Center of Excellence Geopolymer and Green Technology
SPCI	- South Pacific Chemicals Industries
M	- Molar ratio
mm	- Millimeter

©This item is protected by original copyright

## Kajian Fizikal Dan Mekanikal Terhadap Bata Masonry Geopolimer Berasaskan Kaolin

### ABSTRAK

Bata kebiasaannya digunakan sebagai bahan binaan dalam pembinaan dinding. Bata pembinaan konvensional kebiasaannya diperbuat daripada simen Portland, tanah liat dan pasir, yang mana dicampur dan dibentuk dengan pelbagai kaedah dan perlu dikeringkan dan dibakar pada suhu antara 900 hingga 1200 darjah selsius. Proses pengeringan dan pembakaran mengambil masa 2 hingga 4 hari untuk dilakukan. Selain daripada itu, proses penghasilan simen Portland menggunakan tenaga yang tinggi dan turut mengeluarkan 1 hingga 1.2 tan gas karbon dioksida ( $\text{CO}_2$ ) untuk setiap 1 tan simen Portland yang dihasilkan. Pada masa kini, bahan binaan yang baru iaitu simen geopolimer telah menyaksikan perkembangan yang hebat di serata dunia. Ini berpunca daripada isu alam sekitar yang menekan pihak industri untuk menyediakan produk dan bahan binaan yang lebih mesra alam. Matlamat penyelidikan ini adalah untuk menghasilkan produk yang akan memberikan alternatif kepada bata konvensional dengan ciri-ciri yang baik melibatkan penggunaan bahan geopolimer iaitu kaolin, mengurangkan pencemaran alam sekitar dengan menggantikan penggunaan simen Portland dalam industri membuat bata, dan menghasilkan produk guna pakai efektif yang boleh digunakan oleh meningkatkan sifat-sifat produk yang sedia ada. Kajian ini telah dijalankan untuk menghasilkan bata geopolimer berasaskan kaolin dengan menggunakan kaedah pembentukan menggunakan tekanan tanpa proses pembakaran dan penggunaan tenaga yang rendah. Kajian dijalankan pada bata kaolin berasaskan geopolimer dengan mempelbagaikan nisbah pasir terhadap kaolin (4:1 – 8:1, berdasarkan nisbah jisim), nisbah  $\text{Na}_2\text{SiO}_3$  terhadap NaOH (0.2:1 - 0.4:1, berdasarkan nisbah jisim) dan nisbah kaolin terhadap alkali pengaktif (0.5:1 - 1.5:1, berdasarkan nisbah jisim) dengan nilai molariti NaOH, suhu pengawetan dan masa pengawetan yang malar iaitu 8 molar, 80 darjah selsius selama 24 jam. Kekuatan mampatan, ujian penyerapan air, ujian dimensi, dan analisis ketumpatan telah ditetapkan sebagai ciri – ciri mekanikal yang akan diuji pada bata geopolimer berasaskan kaolin. Kekuatan mampatan mencecah 5.87 MPa telah diperolehi dengan nisbah sodium silikat terhadap sodium hidroksida, kaolin terhadap alkali pengaktif, dan pasir terhadap kaolin 0.3:1, 1:1 dan 8:1. Julat ketumpatan bata geopolimer kaolin adalah antara 1636  $\text{kg/m}^3$  hingga 2175  $\text{kg/m}^3$ . Sifat mikrostruktur bata Geopolimer berasaskan kaolin-telah dikaji dengan menggunakan analisis XRD yang mana menunjukkan komponen mineral yang utama dalam bata geopolimer berasaskan kaolin adalah kaolinite dan quartz.

## Physical and Mechanical Studies of Kaolin-Based Geopolymer Masonry Brick

### ABSTRACT

A brick is mainly applied as a building material in construction of walls. Conventional construction bricks are usually made from Portland cement, clay and sand, which are mixed and molded in various method and need to be dried and burned with the temperature range between 900 to 1200 degree centigrade. The drying and firing process takes 2 to 4 days to be done. Other than that, the production of Portland cement consume high energy and can emit 1 to 1.2 ton of carbon dioxide (CO<sub>2</sub>) for every 1 ton of Portland cement product. Nowadays, a novel family of building materials which is geopolymer cement has seen a great development around the world. It is caused by the environmental issues that pressured the industries to manufacture a products and materials that are more environmental friendly. The aim of this research was to produce a product that would provide an alternative to the conventional bricks with a good properties by utilizing a geopolymer material which is kaolin, reduce the pollution of environment by replacing the usage of Portland cement in brick making industry, and produce effectively usable product by enhance the properties of ordinary product. This study has been conducted to produce kaolin-based geopolymer bricks by means of pressure forming without firing procedure and low energy consumptions. The experiments were conducted on kaolin-based geopolymer bricks by varying the ratio of sand-to-kaolin (4:1 - 8:1, by mass of ratio), Na<sub>2</sub>SiO<sub>3</sub>-to-NaOH (0.2:1–0.4:1, by mass of ratio) and kaolin-to-activator (0.5:1– 1.5:1, by mass of ratio) with constant molarity of NaOH, curing temperature and time which is 8 molar, 80 degree celcius for 24 hours. Compressive test, water absorption, dimensional test and density analysis were performed on the kaolin -based geopolymer bricks. Compressive strength up to 5.87 MPa was obtained with ratio of sodium silicate-to-sodium hydroxide, kaolin-to-alkaline activator, and sand-to-kaolin 0.3:1, 1:1 and 8:1 by mass. The density of geopolymer bricks were ranged between 1636 kg/m<sup>3</sup> to 2175 kg/m<sup>3</sup>. The microstructural properties of kaolin-based geopolymer bricks were investigated by using XRD analysis which shows that the major mineral components of kaolin- based geopolymer brick were kaolinite and quartz.



# CHAPTER 1

## INTRODUCTION

### 1.1 Background

Based on previous archaeological studies, the technology of brick is believed began in about the third millennium before century around Middle East (Woods, 2006). In the past, the bricks were made from the remains of mud left after flood that came from the river. The bricks were shaped into brick shape by hand and dry under normal condition (Das, 2010). Modern bricks were made from concrete, sand and lime compared to traditional structures that were built by layering the bricks using mud. Brick is still being used until today in building construction industries because of its characteristic which is high resistant, durable and long lasting when properly maintain.

The brick is mainly applied as a building material in construction of walls. A blend of fine-grain sand, a cementations material such as ordinary Portland cement (OPC) and water were used in production of cement brick which is one of brick types which also called masonry brick. When the mixing of brick cement is still in wet condition, it can be controlled and manipulated like a thick paste. However, when the mixture dried, it hardens and sets, turning into a strong solid bricks. Brick cement can be used in new construction, and also in repainting, in which old cement is carefully removed and replaced to enact repairs. Proper process of producing cement brick can lead to a better quality of brick.

However, with increased activities in construction, deficiency of building materials and construction waste improvements have encouraged the development of new building materials. Conventional construction bricks are usually made from cement, clay and sand, which are mixed and molded in various method and need to be dried and burned with the temperature range between 900 to 1200 degree centigrade and the drying and firing process takes 2 to 4 days to be done. This process consume alot of energy and take a long time before the brick can be used. Other than that, the production of conventional construction brick that used OPC as its main ingredient is a highly energy intense product that generate CO<sub>2</sub> (Habert, d'Espinose de Lacaillerie, & Roussel, 2011).

Due to this problem, many research had been conducted in order to find an alternative to the ordinary construction material which uses alternative raw materials such as kaolin, fly ash, boiler ash and others to be implement as a building and construction materials including brick (Wan Mastura W. I., Kamarudin, Khairul Nizar, Mustafa Al bakri, & Binhussain, 2013; Ferone, Colangelo, Cioffi, Montagnaro, & Santoro, 2011), mortar (Swanepoel & Strydom, 2002; Hardjito, Cheak, & Lee, 2008; Temuujin, VanRiessen, & Mackenzie, 2010), and concrete (Sumajouw, Hardjito, Wallah, & Rangan, 2007; Abdullah, et al., 2011) that lead to the introduction of geopolymer technology in brick production.

The production process of geopolymer bricks consume less energy due to low curing temperature besides low production cost in term of production and less time consuming compared to conventional bricks. The development of geopolymer brick is

an important step towards producing a brick with better performance and environmental friendly material.

The aim of producing this brick is to create the solution with the low cost involved by utilizing a low cost material, reduce the pollution of environment by replacing the usage of Portland cement in brick making industry, and produce effectively usable product by enhance the properties of ordinary product.

## **1.2 Problem Statement**

Conventional bricks need to be dried and burned with the temperature range between 900 – 1200 degree centigrade. The drying and firing process takes 2 to 4 days to be done. This process use alot of energy and take a long time before the brick can be used. Besides that, in Malaysia construction industries, people are too dependent on cement as their construction materials. The production of ordinary Portland cement, which is widely being used in construction such as masonry brick incredibly energy intensive to make and can emit 1 to 1.2 ton of carbon dioxide (CO<sub>2</sub>) for every 1 ton of Portland cement product(Swamy, 2000). This will have a significant impact on the environment. Due to this problem, other alternative has been discovered which the replacement of clay brick to cement brick.

Early 2007, Dr. Henry Liu has come out with a brilliant solution which is producing the fly-ash bricks. Innovative use of fly ash to manufacture high quality building materials will potentially decrease some of the negative environmental impact of coal fired power generation while meeting increasing demands for greener building

materials (NSF Press Release 07-058, 100% Fly Ash Brick is the nation's "Greenest Brick", May 2007). This fly ash brick can reduce the cost of bricks and also can reduce the amount of fly ash that emitted into landfill can save the energy and reduce the pollution.

Geopolymer, which is also known as mineral polymers or inorganic polymer glasses which the chemical compositions of the geopolymer materials resemble to natural zeolitic materials with amorphous microstructure, is a promising new form of inorganic polymer material that could be another good alternative to the ordinary Portland cement in production of cement masonry brick industries. In earlier study, researchers have focused on kaolin as the aluminosilicate source in geopolymer (J., 1999). Later, the utilization of fly ash as aluminosilicate source in producing construction materials became major study areas (Hardjito, Cheak, & Lee, 2008; Sumajouw, Hardjito, Wallah, & Rangan, 2007; Temuujin, VanRiessen, & Mackenzie, 2010; Abdullah, et al., 2011). However the use of kaolin in geopolymer brick production has not been studied in details.

The aim of this research is to produce a product that will create an alternative to the cement masonry brick with a good properties involved by utilizing kaolin as aluminosilicate source, reduce the pollution of environment by replacing the usage of Portland cement in brick making industry, and produce effectively usable product by enhance the properties of ordinary product.

In addition, the use of kaolin is not common in the Malaysia's brick manufacturing sector. This study will be able to enhance the understanding on the

production of kaolin - based geopolymer brick production and suitability of kaolin - based geopolymer brick as a substitute to the conventional masonry brick in the construction industries as a construction material.

### **1.3 Objectives of Study**

The main purpose of the research was to study the development of kaolin based geopolymer mortar brick with geopolymerization process. The main objectives of this study were:

1. To produce kaolin based geopolymer brick by using geopolymer brick making machine.
2. To obtain the optimum ratios and identify the effect of different sand/kaolin, activators ( $\text{Na}_2\text{SiO}_3/\text{NaOH}$ ) and kaolin/activator ratio on the mechanical properties such as compressive strength, density and water absorption of kaolin based geopolymer brick.
3. To identify the correlation between compressive strength, water absorption and density of kaolin based geopolymer brick.

### **1.4 Scope of Research**

This study focuses on the production and properties of geopolymer brick made with kaolin as its geopolymer raw material. The geopolymer raw material that was used in this study which is kaolin was locally supplied by Kaolin Industries Sdn. Bhd. The kaolin based geopolymer brick was produced by mixing sand, kaolin and alkaline

solution consist of sodium silicate and sodium hydroxide with various ratios by using geopolymer brick making machine. Then the geopolymer samples had been tested in the laboratory to determine its compressive strength, density and water absorption properties in order to identify the optimum ratios of all the parameters. The whole testing was done accordance to the standard. The morphology of the original kaolin and kaolin based geopolymer brick with different ratios sand to kaolin, kaolin to activator and  $\text{Na}_2\text{SiO}_3$  to  $\text{NaOH}$  was studied by using XRD analysis. The correlation between compressive strength, water absorption and density of kaolin based geopolymer brick were also studied.

## **1.5 Organization of the Thesis**

Chapter 1 presents the background of the research work, the problem statement that lead to the research work, the objectives of the current study and also the scope of the research work.

Chapter 2 review the literatures of the potential application of kaolin to be used in production of geopolymer brick by using geopolymerization process. This chapter also brief literatures about different types of brick, its classification, size of brick that is commonly produced, and also the application and advantages of the brick. This chapter also discusses about geopolymer technology and its suitability in brick production with much focussing on the material used in producing kaolin-based geopolymer brick, the production and also properties of the brick.

Chapter 3 describes the experimental methods to prepare kaolin-based geopolymer brick, the production process and the experimental testing and analysis method conducted to evaluate the engineering properties of the kaolin-based geopolymer brick accordance to standard.

Chapter 4 presents the result and discussion of the analysis. The result and discussion include the characterization of raw materials, microstructure study of kaolin-based geopolymer brick and the effect of each parameters which is different Sand/Kaolin, activators ( $\text{Na}_2\text{SiO}_3/\text{NaOH}$ ) and Kaolin/Activator ratios to the properties of the kaolin-based geopolymer brick. The correlation between kaolin-based geopolymer properties were also discussed in this chapter.

Chapter 5 summarize and conclude the result of this study and the suggestions and recommendation for future research.

## **CHAPTER 2**

### **LITERATURE REVIEW**

#### **2.1 Introduction**

This chapter presents a short review of bricks available in the market, their specifications and classifications. This will be followed by the review on the background of geopolymer technology, application of geopolymer in brick production and also the reaction in geopolymer process. This chapter will also discussing the materials in kaolin - based geopolymer brick production, the curing process of geopolymer brick, the application and advantages of the brick, and also the engineering properties of bricks in terms of compressive strength, water absorption, dimension tolerances and density of the bricks.

#### **2.2 Definition of Brick**

Brick is a solid or hollow manufactures masonry unit, usually formed into a small rectangular prism. Brick selection is made according to the specific application in which the brick will be used. Standards for brick cover specific uses of brick and classify the brick by performance characteristics. The performance criteria include strength, durability and aesthetic requirements. Selection of the proper specification and classification within that specification, along with proper design and construction, should result in expected performance.