



**CHARACTERISTICS AND PROPERTIES OF
ACTIVATED CARBON FROM BAMBOO FILLED
STYRENE BUTADIENE RUBBER (SBR)
VULCANIZATES**

by

**NOR MUNIRAH BT ROHAIZAD
(1430411238)**

A thesis submitted in fulfillment of the requirements for the degree of
Master of Science in Materials Engineering

**School of Materials Engineering
UNIVERSITI MALAYSIA PERLIS**

2016

UNIVERSITI MALAYSIA PERLIS

DECLARATION OF THESIS

Author's full name : NOR MUNIRAH BT ROHAIZAD
Date of birth : 27 DECEMBER 1989
Title : CHARACTERISTICS AND PROPERTIES OF ACTIVATED CARBON
FROM BAMBOO FILLED STYRENE BUTADIENE RUBBER (SBR)
VULCANIZATES.
Academic Session : 2014/2015

I hereby declare that the thesis becomes the property of Universiti Malaysia Perlis (UniMAP) and to be placed at the library of UniMAP. This thesis is classified as :

- CONFIDENTIAL** (Contains confidential information under the Official Secret Act 1972)*
- RESTRICTED** (Contains restricted information as specified by the organization where research was done)*
- OPEN ACCESS** I agree that my thesis is to be made immediately available as hard copy or on-line open access (full text)

I, the author, give permission to the UniMAP to reproduce this thesis in whole or in part for the purpose of research or academic exchange only (except during a period of _____ years, if so requested above).

Certified by:

SIGNATURE

891227-14-6154

(NEW IC NO. / PASSPORT NO.)

Date : _____

SIGNATURE OF SUPERVISOR

DR. NIK NORIMAN BIN ZULKEPLI

NAME OF SUPERVISOR

Date : _____

NOTES : * If the thesis is CONFIDENTIAL or RESTRICTED, please attach with the letter from the organization with period and reasons for confidentiality or restriction.

ACKNOWLEDGEMENT

Alhamdulillah, all praises to Allah for the strength and His blessing in completing this thesis. A special appreciation goes to the Universiti Malaysia Perlis (UniMAP) and Ministry of Higher Education (MOHE) for sponsoring and providing the financial scholarship for this research work.

It is with immense gratitude that I acknowledge the support and help of my supervisor, Dr. Nik Noriman Zulkepli, for his guidance and constant support in my academic work. His invaluable help, constructive comments and suggestions throughout the experimental stage of this thesis have contributed to the success of this research. I also wish to express my deepest gratitude to my second supervisor, Mr. Muhammad Salihin Zakaria for his encouragement and advice to improve the quality of this thesis.

My special thanks to Dr. Khairul Rafeizi (Dean) and all the technical staff of the School of Materials Engineering, UniMAP for their support and technical advice especially in handling the research facilities. My utmost appreciation goes to Mr. Nasir, Mr. Zaidi, Mr. Hadzrul, Mr. Azmi and Mr. Chek Idrus for their valuable assistance.

I am indebted to my colleagues especially Hafizah, Afiratul, Fatin, Aina, Athirah, Syafiqah and Hidayah for their moral support and motivation whenever I needed it. In addition, my acknowledgement goes to the assistance and inspiration of all those who contributed directly or indirectly to this research effort.

Last but not least, I would like to dedicate this thesis to my parents, Rohaizad Bin Husain and Salmi Binti Kassim and my family who have always stood by me especially during my hard time. Their love, understanding and encouragement are always appreciated.

Nor Munirah Bt Rohaizad

April 2016

TABLE OF CONTENTS

THESIS DECLARATION	ii
ACKNOWLEDGEMENT	iii
TABLE OF CONTENTS	iv
LIST OF TABLES	x
LIST OF FIGURES	xi
LIST OF ABBREVIATIONS	xiii
LIST OF NOMENCLATURES	xv
LIST OF SYMBOLS	xvi
ABSTRAK	xvii
ABSTRACT	xviii
CHAPTER 1: INTRODUCTION	
1.1 General Background	1
1.2 Problem Statement	3
1.3 Objectives	4
1.4 Scope of Study	5
1.5 Structure of Thesis	6

CHAPTER 2: LITERATURE REVIEW

2.1	<i>Gigantochloa Scortechiini</i> (Bamboo)	8
2.2	Styrene Butadiene Rubber	10
2.3	Carbon Black	11
2.3.1	Influence of Carbon Black on Rubber Reinforcement	13
2.4	Activated Carbon	16
2.4.1	Factors Affecting Properties of Activated Carbon	19
2.4.1.1	Carbonization temperature	19
2.4.1.2	Heating rate	20
2.4.2	Influence of Activated Carbon in Rubber Reinforcement	21
2.5	Bio-based Filler Reinforcement of Elastomers	22
2.5.1	Effect of Filler Loading on Cure Characteristics of Vulcanizates	23
2.5.2	Effect of Filler Loading on Mechanical Properties of Vulcanizates	24
2.6	Compatibilization of Rubber	26

CHAPTER 3: METHODOLOGY

3.1	Introduction	29
3.2	Carbonization of Raw Bamboo	29
3.3	Activation Process	30
3.4	Physical Characterization of Fillers	31
3.4.1	Surface Area Measurement	31
3.5	Chemical Characterization of Fillers	31

3.5.1	Carbon, Hydrogen and Nitrogen (CHN) Characterization	31
3.5.2	X-ray Fluorescence (XRF) Characterization	32
3.5.3	Fourier Transform Infrared (FTIR) Characterization	32
3.6	Thermal Properties	32
3.6.1	Thermogravimetric Analysis (TGA)	32
3.7	Surface Morphology	33
3.8	Compounding Materials	33
3.9	Preparation of Rubber Compounds	34
3.9.1	Carbonized Bamboo and Bamboo Activated Carbon Filled SBR Compounds	34
3.9.2	TOR Compatibilized SBR Vulcanizates	35
3.10	Cure Characteristics, Physical and Tensile Properties	36
3.10.1	Cure Characteristics	36
3.10.2	Hardness	37
3.10.3	Resilience	37
3.10.4	Swelling Test and Crosslink Density	38
3.10.5	Tensile Properties	39
3.11	Experimental Chart	40
CHAPTER 4: CHARACTERIZATION OF RAW BAMBOO, CARBONIZED BAMBOO AND BAMBOO ACTIVATED CARBON		
4.1	Introduction	41
4.2	Physical Characteristics	42

4.2.1	Surface Area	42
4.3	Chemical Characteristics	44
4.3.1	Char Yield and Carbon, Hydrogen and Nitrogen Analysis	44
4.3.2	X-ray Fluorescence (XRF) Analysis	46
4.3.3	Fourier Transform Infrared (FTIR) Analysis	48
4.4	Thermal Properties	52
4.4.1	TGA Analysis	52
4.5	Surface Morphology	53
4.6	Summary	57
CHAPTER 5: THE EFFECTS OF FILLER LOADING ON THE PROPERTIES OF CARBONIZED BAMBOO AND BAMBOO ACTIVATED CARBON FILLED STYRENE BUTADIENE RUBBER (SBR) VULCANIZATES		
5.1	Introduction	59
5.2	Cure Characteristics	60
5.3	Physical Properties	64
5.3.1	Crosslink density	64
5.3.2	Hardness	65
5.3.3	Resilience	66
5.4	Tensile Properties	67
5.5	Morphology	70
5.6	Summary	75

CHAPTER 6: EFFECTS OF TRANS-POLYOCTYLENE (TOR) AS COMPATIBILIZER ON THE PROPERTIES OF BAMBOO ACTIVATED CARBON FILLED STYRENE BUTADIENE RUBBER (SBR) VULCANIZATES

6.1	Introduction	76
6.2	Cure Characteristics	77
6.3	Physical Properties	79
6.3.1	Crosslink density	79
6.3.2	Hardness	80
6.3.3	Resilience	81
6.4	Tensile Properties	82
6.5	Morphology	84
6.6	Summary	87

CHAPTER 7: CONCLUSION AND RECOMMENDATIONS

8.1	Conclusion	88
8.2	Recommendations	89

REFERENCES

LIST OF PUBLICATIONS

LIST OF AWARDS

LIST OF TABLES

NO.		PAGE
2.1	Effects of CB on Rubber Properties	14
2.2	IUPAC Classification of Pores	17
3.1	Parameters for Carbonization Process	30
3.2	Compounding Ingredients and Its Function and Suppliers	34
3.3	Formulations for Carbonized Bamboo and Bamboo AC Filled SBR Vulcanizates	35
3.4	Formulations for Compatibilized SBR Vulcanizates	36
4.1	BET Surface Area, Micropore Area and Micropore Volume of Carbonized Bamboo and Bamboo Activated Carbon	44
4.2	Percentage of Yield and Elemental Analysis of Carbonized Bamboo and Bamboo Activated Carbon	45
4.3	Elemental Analysis of Raw Bamboo, Carbonized Bamboo and Bamboo Activated Carbon	47
5.1	Cure Characteristics of SBR-GV and SBR-CGS Vulcanizates	63
5.2	Cure Characteristics of SBR-GV and SBR-AC Filled SBR Vulcanizates	63
6.1	Cure Characteristics of Uncompatibilized and Compatibilized SBR Vulcanizates	77

LIST OF FIGURES

NO.		PAGE
2.1	Bamboo (<i>Gigantochloa Scortechiini</i>)	9
2.2	Chemical Structure of SBR	10
2.3	Particle and Structure of CB	11
2.4	Effect of CB Loading on the 300 % Modulus and Elongation at Break of Rubber Compounds	16
2.5	Mechanical properties of raw N330-f and N330-f-CO ₂ filled SBR	22
2.6	Chemical Structure of TOR	27
3.1	Summary of Experimental Procedures	41
4.1	FTIR Spectra for Raw Bamboo	48
4.2	FTIR Spectra for Carbonized Bamboo at Heating Rate 5°C/min	50
4.3	FTIR Spectra for Carbonized Bamboo at Heating Rate 15°C/min	50
4.4	FTIR Spectrum of Bamboo Activated Carbon	51
4.5	TGA and DTG curves of Raw Bamboo	52
4.6	Surface Morphology of Raw Bamboo	53
4.7	Surface Morphology of Carbonized Bamboo at Heating Rate of 5 °C/min	55
4.8	Surface Morphology of Carbonized Bamboo at Heating Rate of 15 °C/min	56
4.9	Surface Morphology of Bamboo Activated Carbon	57
5.1	Effects of Filler Loading on Crosslink Density of Filled SBR Vulcanizates	65
5.2	Effects of Filler Loading on Hardness of Filled SBR Vulcanizates	66
5.3	Effects of Filler on Resilience of Filled SBR Vulcanizates	67
5.4	Effects of Filler Loading on Tensile Modulus of Filled SBR Vulcanizates	68

5.5	Effects of Filler Loading on Tensile Strength of Filled SBR Vulcanizates	69
5.6	Effects of Filler Loading on Elongation at Break of Filled SBR Vulcanizates	70
5.7	SEM of Tensile Fracture Surface of SBR-GV Vulcanizate at magnification 300x	71
5.8	SEM of Tensile Fracture Surface of SBR-CGS Vulcanizates (a) and (b) at 10 phr of Carbonized Bamboo and (c) and (d) at 50 phr of Carbonized Bamboo at Magnification 300x and 1000x	72
5.9	SEM of Tensile Fracture Surface of SBR-AC Vulcanizates (a) and (b) at 10 phr of Carbonized Bamboo and (c) and (d) at 50 phr of Carbonized Bamboo at Magnification 300x and 1000x	74
6.1	Effects of TOR Loading on Crosslink Density of SBR-TOR Vulcanizates	79
6.2	Effects of TOR Loading on Hardness of SBR-TOR Vulcanizates	80
6.3	Effects of TOR Loading on Resilience of SBR-TOR Vulcanizates	81
6.4	Effects of TOR Loading on Tensile Modulus of SBR-TOR Vulcanizates	82
6.5	Effects of TOR Loading on Tensile Strength of SBR-TOR Vulcanizates	83
6.6	Effects of TOR Loading on Elongation at Break of SBR-TOR Vulcanizates	84
6.7	SEM of Tensile Fracture Surface of SBR-TOR Vulcanizates (a) at 2 phr of TOR and (b) at 8 phr of TOR at Magnification 300x	85
6.8	SEM of Tensile Fracture Surface of SBR-TOR Vulcanizates (c) at 2 phr of TOR and (d) at 8 phr of TOR at Magnification 1000x	86

LIST OF ABBREVIATIONS

AC	Activated Carbon
ASTM	American Society for Testing And Materials
BCP	Bamboo Charcoal Powder
BET	Brunauer–Emmett–Teller
CB	Carbon Black
CC	Carbonized Coir
CHN	Carbon, Hydrogen, Nitrogen
CRI	Cure Rate Index
CSS	Cherry Seed Shell
DTG	Derivative Thermogravimetric
E _B	Elongation at Break
ENR	Epoxidized Natural Rubber
EPDM	Ethylene Propylene Diene Monomer
FTIR	Fourier Transform Infrared
M ₁₀₀	Modulus at 100 % of Elongation
M _H	Maximum Torque
M _L	Minimum Torque
N330	Carbon Black
NBR	Acrylonitrile Butadiene Rubber
NR	Natural Rubber
phr	Part per hundred rubber
PKH	Palm Kernel Husk
SBR	Styrene Butadiene Rubber

SBR-AC	AC Filled SBR Vulcanizte
SBR-CGS	CB Filled SBR Vulcanizate
SBR-GV	Gum Vulcanizate
SBR-TOR	TOR Compatibilized SBR Vulcanizate
SEM	Scanning Electron Microscopy
Semi-EV	Semi-Efficient Vulcanization
t_{c90}	Cure Time
TGA	Thermogravimetric Analysis
TMTD	Tetramethyl Thiuram Disulfide
TOR	Trans-Polyoctylene Rubber
t_{s2}	Scorch Time
XRF	X-Ray Fluorescence

©This item is protected by original copyright

LIST OF NOMENCLATURES

CaO	Calcium oxide
CO ₂	Carbon dioxide
CuO	Copper oxide
Fe ₂ O ₃	Ferum (II) oxide
H ₃ PO ₄	Phosphoric acid
K ₂ O	Potassium oxide
KBr	Potassium bromide
KOH	Potassium hydroxide
MnO	Manganese oxide
NaOH	Sodium hydroxide
P ₂ O ₅	Phosphorus pentoxide
Pd	Palladium
SO ₃	Sulfur trioxide
Si	Silica
SiO ₂	Silica dioxide
ZnO	Zinc oxide
ZnCl ₂	Zinc chloride

LIST OF SYMBOLS

%	Percentage
°C	Degree Celcius
°C/min	Degree Celcius per minute
Å	Armstrong
nm	Nanometer
µm	Micrometer
g	Gram
mg	Miligram
cm ⁻¹	Per centimeter
mL/min	Milliliter per minute
lb-in	Pound inch
mm/min	Milimeter per minute
kN	Kilo Newton
min	Minute
dN-min	Desi Newton minute
min ⁻¹	Per minute
MPa	Megapascal
m ² /g	Meter square per gram
cm ³ /g	Centimeter cube per gram

Pencirian dan Sifat-sifat Karbon Diaktif daripada Buluh Terisi Vulkanisat Getah Stirena Butadiena (SBR)

ABSTRAK

Dalam kajian ini, karbon buluh dan karbon diaktif (AC) buluh telah disediakan melalui proses karbonisasi dan proses pengaktifan kimia menggunakan kalium hidroksida (KOH) sebagai ejen pengaktifan. Proses karbonisasi dijalankan pada suhu karbonisasi yang berbeza (250, 450 dan 650 °C) pada kadar pemanasan 5 dan 15 °C / min. Semakin meningkat suhu karbonisasi, peratusan hasil menurun, walaubagaimanapun kandungan karbon meningkat. Luas permukaan BET karbon buluh meningkat dengan peningkatan suhu karbonisasi dan lebih banyak liang terbentuk seperti yang ditunjukkan dalam mikrograf SEM. Karbon buluh yang dihasilkan pada suhu 650 °C dengan kadar pemanasan 15 °C / min menunjukkan potensi yang paling tinggi untuk menghasilkan AC buluh, dan kemudiannya digunakan sebagai pengisi dalam sebatian SBR disebabkan oleh kandungan karbon yang lebih tinggi dengan luas permukaan BET lebih besar. Seterusnya, karbon buluh dan karbon diaktif buluh terisi sebatian SBR (SBR-CGS dan SBR-AC) dengan pelbagai kandungan pengisi dari 10 hingga 50 bahagian per ratus getah (bsg) telah disediakan. Kesan kandungan pengisi terhadap ciri-ciri pematangan, sifat fizikal dan tegangan ditentukan. Hasil kajian menunjukkan penambahbaikan dalam ciri-ciri pematangan bagi kedua-dua vulkanisat SBR-CGS dan SBR-AC. Ciri-ciri fizikal bagi kedua-dua vulkanisat terisi SBR bertambah baik dari segi kenaikan dalam kekerasan dan susutan dalam daya tahan dengan kandungan pengisi yang meningkat. Selain itu, sifat tegangan untuk kedua-dua vulkanisat SBR-CGS dan SBR-AC juga meningkat di mana kekuatan tegangan dan modulus tegangan serta pemanjangan pada takat putus (E_B) meningkat. Kajian morfologi menunjukkan bahawa kedua-dua pengisi tersebar secara homogen dalam SBR vulkanisat, menyebabkan interaksi pengisi-getah yang baik dan seterusnya meningkatkan sifat tegangan. Perbandingan antara kedua-dua vulkanisat terisi SBR menunjukkan bahawa vulkanisat SBR-AC mempunyai sifat-sifat yang lebih baik daripada vulkanisat SBR-CGS disebabkan oleh keliangan pengisi AC buluh. Vulkanisat SBR-AC yang mengandungi 50 bsg AC buluh mempamerkan sifat-sifat optimum dan sebatian tersebut dipilih untuk ditambah dengan *trans-polyoctylene rubber* (TOR) sebagai bahan penyerasian. Kemasukan TOR ke dalam vulkanisat SBR-AC menunjukkan sedikit kenaikan dalam kekuatan tegangan dan pengurangan dalam kekerasan dan modulus tegangan dengan peningkatan kandungan bahan penyerasian dari 2 hingga 8 bsg.

Characteristics and Properties of Activated Carbon from Bamboo Filled Styrene Butadiene Rubber (SBR) Vulcanizates

ABSTRACT

In this study, carbonized bamboo and bamboo activated carbon (AC) were prepared via carbonization process and chemical activation process using potassium hydroxide (KOH) as activating agent. Carbonization process was conducted at different carbonization temperature (250, 450 and 650 °C) with heating rate of 5 and 15 °C/min. As carbonization temperature increased, the percentage of char yield decreased, however the carbon content increased. The BET surface area of carbonized bamboo increased with increasing carbonization temperature and more pores were created as shown in SEM micrographs. Carbonized bamboo produced at 650 °C with heating rate 15 °C/min showed the highest potential to produce bamboo AC, subsequently used as filler in SBR compounds owing to its higher carbon content with higher BET surface area. Next, carbonized bamboo and bamboo activated carbon filled SBR (SBR-CGS and SBR-AC) compounds with varying filler loading from 10 to 50 part per hundred rubber (phr) were prepared. The effects of filler loading on the cure characteristics, physical and tensile properties were determined. Results showed that the improvement in cure characteristics for both SBR-CGS and SBR-AC vulcanizates. The physical properties of both filled SBR vulcanizates improved in terms of increment in hardness and decrement in resilience as the filler loading increased. Besides, the tensile properties for both SBR-CGS and SBR-AC vulcanizates also enhanced which the tensile strength and tensile modulus as well as elongation at break (E_B) increased. The morphology studies showed that both filler dispersed homogeneously in SBR compounds, resulted in good filler-rubber interaction and consequently improved the tensile properties. Comparing both filled SBR vulcanizates, it showed that SBR-AC vulcanizates have better properties than SBR-CGS vulcanizates due to the porosity of bamboo AC filler. SBR-AC vulcanizate with 50 phr of bamboo AC exhibited optimum properties and was selected to be added with trans-polyoctylene (TOR) as compatibilizer. Incorporation of TOR into SBR-AC vulcanizates showed slightly increment in tensile strength and reduction in hardness and tensile modulus as the compatibilizer loading increased from 2 to 8 phr.

CHAPTER 1

INTRODUCTION

1.1 General Background

Carbon black (CB) is mainly used in rubber industry for various purposes, of which the most important are reinforcement, reduction in material costs and improvement in processing (Pal et al., 2011). Meanwhile, for thermoplastics products, CB are used as ultraviolet stabilizer, electrical conductor and also used to increase weather resistance and improve mechanical properties of the composites.

It was expected that the global carbon black market was projected to reach 12.2 million metric tons in 2015 according to the “Carbon Black: A Global Strategic Business Report”. The largest consumer was Asia-Pacific which contributes 37% of total production of carbon black. About 90% of carbon black is used in the rubber industry as reinforcing filler in a variety of products including tires, tubes, cables and other rubber goods (“Carbon Black - World Consumption,” n.d).

In rubber technology, the mixing of filler is extremely important especially for the synthetic rubber such as styrene butadiene rubber (SBR), ethylene propylene diene monomer rubber (EPDM) and others. The addition of filler produces improvements in mechanical properties such as tensile strength, tear resistance, abrasion resistance and modulus (Long, 1985). Reinforcing fillers like CB must be added to the SBR to develop the best properties because SBR has low strength due to the fact that SBR does not

crystallize on stretching unlike NR (Schwartz, 2002). For example, the strength of vulcanized unfilled styrene butadiene rubber (SBR) is about 2.0–3.0MPa. But when reinforcing carbon black is added (40–60 pphr) into the rubber, the tensile strength increases by a factor of 10 to 27–30 MPa (Azemi, 2013).

It is well known that CB is the most effective reinforcing filler for the rubber composites (Mai & Yu, 2006). It is available in a variety of grades, each grade having different physical and chemical characteristics and therefore affording a different property profile to rubber. The highly reinforcing carbon black fillers are generally small in particle size, chemically active and have surfaces which are both porous and very irregular in shape (Hewitt & Ciullo, 2007). These characteristics are desirable to maximize the surface area of contact between rubber and filler.

In many years, a lot of researchers have gained interest in using natural fibers or biomass as to replace commercial filler that is CB in rubber compound. Numerous studies have been done to produce alternative CB from inexpensive, obtainable and renewable raw materials such as bagasse (Osarenmwinda & Abode, 2010), coconut shell (Egwaikhide et al., 2008), coir (Aguale & Madufor, 2012), kernel husk (Egwaikhide et al., 2013) and others. The reason of using natural fibers is because they have high carbon content and low ash content. Though, there are not many reports on the utilization of activated carbon (AC) as filler in rubber compounding which might have potential in replacing commercial carbon black. This is due to the fact that most of the applications of AC are employed as adsorbent since AC is well-known as porous materials with high surface area. Therefore, in this study, AC from *Gigantochloa Scortechiini* (bamboo) is produced by carbonization and chemical activation process and acts as bio-based filler in rubber.

1.2 Problem Statement

Carbon black (CB) may contribute greenhouse gas emission which is harmful to the environment. Besides, CB is relatively expensive since the main source of CB is petroleum which is limited and non-renewable resource. Therefore, biomass is used as cheaper alternative replacing commercial CB due to its availability and environmental friendly. There is a limited number of works that are concerned with the utilization of activated carbon from natural fibers or agricultural wastes especially *Gigantochloa Scortechiini* (bamboo) as bio-based filler for rubber compounding. It is needed to put additional effort to clarify the influences of activated carbon in rubber. For making better use of char obtained to produce activated carbon, the composition, surface area and pore structure should be investigated. Those char characteristics were influenced by carbonization conditions. Thus, the bivariate analysis was carried out to investigate the combined effect of carbonization temperature and heating rate on the char characteristic.

Due to the fact that the unfilled SBR has low strength, SBR needs filler for better properties. The performance of filled synthetic rubber may affect either by the rubber matrix itself or the filler that being incorporated into the matrix. The effects of filler may attribute to the particle size, structure and loading of the filler. Hence, the effects of filler loading on the cure characteristics and physical and tensile properties of SBR vulcanizates will be investigated in order to determine the optimum filler loading which gives better properties.

Nevertheless, the compatibility between natural fiber and rubber matrix might be not so good due to high moisture content in fiber that lead to agglomeration of filler, thus

affect the properties of rubber vulcanizate. Therefore, incorporation of compatibilizer may improve the interaction between filler and rubber.

1.3 Objectives

The aims of the study were:

1. To determine the characteristics and properties of carbonized bamboo and activated carbon from *Gigantochloa Scortechiini* (bamboo) at different parameters of carbonization; carbonization temperature and heating rate using CHN, BET, XRF, and FTIR analysis.
2. To examine the effects of filler loading on the cure characteristics, physical and tensile properties and morphology of carbonized bamboo and bamboo activated carbon filled SBR vulcanizates.
3. To evaluate the effects of trans-polyoctylene rubber (TOR) as a compatibilizer on the cure characteristics, physical and tensile properties and morphology of compatibilized SBR vulcanizates.

1.4 Scope of Study

In this research, the production of bamboo activated carbon (AC) was carried out via chemical activation method. The process involved the carbonization and activation. The raw materials underwent the carbonization process by varying the carbonization temperature (250, 450 and 650 °C) and heating rate (5 and 15 °C/min). Several analyses were carried out to analyze the carbonized bamboo. The characterizations performed includes physical characteristics like surface area; chemical characteristics such as elemental analysis and thermal analysis and also morphology.

Based on the characteristics of the carbonized bamboo, carbonized bamboo produced at 650 °C and 15 °C/min was selected to be activated. The carbonized materials were impregnated with activating agents. Potassium hydroxide (KOH) was used as activating agent. Then, the activation process took place which the carbonized materials burnt in furnace at operating parameters of 700 °C and 15 °C/min.

The next stage involves the compounding of the filled SBR vulcanizates using carbonized bamboo and bamboo AC as fillers. The optimum loading of filler for the filled SBR vulcanizates was identified by considering the best properties exhibited and then trans-polyoctylene rubber (TOR) was added as a compatibilizer. The incorporation of TOR is to improve the filler-rubber interaction, yet enhance the properties of the vulcanizates.

1.5 Structure of Thesis

This thesis is divided into eight chapters.

Chapter 1 included a brief introduction on carbon black and its reinforcement effect in rubber. The issues of production of CB commercially and its drawbacks generate the ideas and energies to this research work were stated. The main objectives and the general flow of the whole study were also carefully outlined.

Chapter 2 comprised literature review on the reinforcement of CB and bio-based filler in both natural and synthetic rubbers. A literature survey was done on various published works on commercial CB and carbonized agricultural wastes filled in rubbers.

Chapter 3 covered the methodology of the experimental employed in this study, including characterization of materials, testing on the vulcanizates as well as any other processing techniques involved in generating data that were presented in the study.

Chapter 4 presented the characteristics of raw bamboo (*Gigantochloa Scortechiini*), carbonized bamboo and bamboo activated carbon. All the characteristics including physical, chemical characteristics and surface morphology were reported.

Chapter 5 reported the effects of carbonized bamboo filler loading on the cure characteristics, physical and tensile properties and morphology of the filled SBR vulcanizates.

Chapter 6 encompassed the effects of bamboo activated carbon filler loading on the cure characteristics, physical and tensile properties and morphology of the filled SBR vulcanizates.

Chapter 7 reported the effects of trans-polyoctylene rubber (TOR) as a compatibilizer on the cure characteristics, physical and tensile properties and morphology of the filled SBR vulcanizates.

Chapter 8 obtained some concluding remarks on the present work as well as several suggestions for future work.

©This item is protected by original copyright