



**SYNTHESIS, CHARACTERIZATION AND  
PROPERTIES OF LOW DENSITY  
POLYETHYLENE FILLED WITH REDUCED  
GRAPHITE OXIDE**

by

**TOH GUAT YEE  
1340411005**

A thesis submitted in fulfillment of the requirements for the degree of  
Doctor of Philosophy

**School of Materials Engineering  
UNIVERSITI MALAYSIA PERLIS**

2018

UNIVERSITI MALAYSIA PERLIS

**DECLARATION OF THESIS**

Author's Full Name : TOH GUAT YEE  
Title : SYNTHESIS, CHARACTERIZATION AND PROPERTIES OF LOW DENSITY POLYETHYLENE FILLED WITH REDUCED GRAPHITE OXIDE  
Date of Birth : 20 MAY 1988  
Academic Session : 2018/2019

I hereby declare that this thesis becomes the property of Universiti Malaysia Perlis (UniMAP) and to be placed at the library of UniMAP. This thesis is classified as:

**CONFIDENTIAL** (Contains confidential information under the Official Secret Act 1997)\*

**RESTRICTED** (Contains restricted information as specified by the organization where research was done)\*

**OPEN ACCESS** I agree that my thesis to be published as online open access (Full Text)

I, the author, give permission to reproduce this thesis in whole or in part for the purpose of research or academic exchange only (except during the period of \_\_\_\_\_ years, if so requested above)

Certified by:

**SIGNATURE**

**SIGNATURE OF SUPERVISOR**

880520-07-5152

ASSOC. PROF. DR. ONG HUI LIN

**(NEW IC NO. /PASSPORT NO.)**

**NAME OF SUPERVISOR**

Date: 17 June 2018

Date: 17 June 2018

**NOTES** : \* If the thesis is CONFIDENTIAL or RESTRICTED, please attach with the letter from the organization with the period and reasons for confidentiality or restriction.

## ACKNOWLEDGMENT

This day I reach the milestone of my PhD. with the culmination of the thesis. I believe it has been a shower of blessings from numerous well-wishers of world, which has kept me motivated to run this marathon of miles. And I would like to use this opportunity to thank all of them for standing in my side and helping me in this endeavour in all possible ways.

I do not think any dictionary would provide me a suitable word to express what my supervisor Assoc. Prof. Dr. Ong Hui Lin means to me. She made her best efforts to shape me into a research scholar, and embedded in me all the best qualities, which only a teacher can. She always provided new insights to science to make me work in best befitting manner and keeping me motivated through all hurdles. On a lighter note, I was scolded numerous times and all her scolding was blessings in disguise.

I would like to express my profound gratitude to my co-supervisor, Prof. Hazizan Md Akil, from School of Material and Mineral Resources Engineering, Universiti Sains Malaysia and Dr. Janet Lim Hong Ngee, Department of Chemistry Faculty of Science, Universiti Putra Malaysia for their unending expertise and guidance throughout the past five years.

On the personal front, I would like to take this opportunity to fondly thank to Prof. Ruey-an Doong and all the laboratories member from Institute of Environmental Engineering, National Chiao Tung Univeristy, Taiwan for providing me all the necessary facilities during my research work, especially to the members of post-doctoral in the lab, Dr. Kartick Bindumadhawan, Dr. Ankan Dutta Chowdhury, Dr. Pei-Yi Chang and Dr. Manchal Chaudhary. I also express my deep regards to the lab members in Taiwan, Dr. Rama Shanker Sahu, Akhilesh Babu Ganganboina, Binh Nguyen and Jia-wen Hsu for sharing priceless friendship and helping in various ways for successful completion of my work. Heart felt gratitude on their warm affection and support.

Our lab has always been full of fun and frolic between times of serious work. And I have enjoyed many light moments with my labmates. I sincerely thank to Anis Sofiah, Muhammad Safwan Mohaiyiddin, Nik Nur Azza, and Owi Wei Tieng for everything they have been doing for me.

No words are enough to express my gratitude to all my relatives and my family for their blessings and wishes that I could reach so far. Special thanks to my parents for their love, affection and inspirations. They have spent every bit to give my best in life and have prayed every moment for my betterment so that I could concentrate in my research.

At the end, I would like to sincerely thank all my lecturers and professors of my alma meter. I thank God for giving me strength and energy to successfully complete my work and I pray for more knowledge, wisdom, energy and well-being of my world.

## TABLE OF CONTENTS

	<b>PAGE</b>
<b>DECLARATION OF THESIS</b>	<b>i</b>
<b>ACKNOWLEDGMENT</b>	<b>ii</b>
<b>TABLE OF CONTENTS</b>	<b>iii</b>
<b>LIST OF TABLES</b>	<b>viii</b>
<b>LIST OF FIGURES</b>	<b>ix</b>
<b>LIST OF ABBREVIATIONS</b>	<b>xiii</b>
<b>LIST OF SYMBOLS</b>	<b>xv</b>
<b>LIST OF Equations</b>	<b>xvi</b>
<b>ABSTRAK</b>	<b>xvii</b>
<b>ABSTRACT</b>	<b>xviii</b>
<b>CHAPTER 1 : INTRODUCTION</b>	<b>1</b>
1.1 Nanocomposites: Current Status, Challenges and Future	1
1.2 Graphite Oxide based Thermoplastic Nanocomposites	3
1.3 Problem Statement	5
1.4 Objectives of study	6
1.5 Scope of Study	7
1.6 Outline of Thesis Structure	9
<b>CHAPTER 2 : LITERATURE REVIEW</b>	<b>11</b>
2.1 Introduction	11
2.2 Overview of graphene oxide	12
2.2.1 History and improvement of graphene oxide	13
2.2.2 Differences between graphene oxide and graphite oxide	14

2.2.3	Synthesis method	15
2.2.4	Structural features of graphene oxide	17
2.2.5	Reduction of graphite oxide	20
2.2.5.1	Thermal annealing process	21
2.2.5.2	Low temperature thermal reduction	22
2.2.5.3	Chemical reduction	25
2.3	Nanocomposites from polyolefin and reduced graphite oxide	28
2.3.1	Polyolefin – Polyethylene	29
2.3.2	Polyethylene nanocomposites	30
2.4	Overview of polyethylene and its nanocomposites degradation	32
2.4.1	Types of degradation techniques	32
2.5	Properties evaluation towards polyethylene nanocomposites	36
2.5.1	Mechanical properties	36
2.5.2	Thermal properties	37
2.5.3	Optical properties	38
2.5.4	Gas barrier properties	38
2.6	Advantages and application of polyethylene based nanocomposites	39
<b>CHAPTER 3 : METHODOLOGY</b>		<b>40</b>
3.1	Materials	40
3.2	Synthesis of Graphite Based Materials and Its Characterization	40
3.2.1	Synthesis of graphite oxide	40
3.2.2	Synthesis of reduced graphite oxide	41
3.2.3	Characterization on synthesized graphite oxide and reduced graphite oxide	41
3.2.3.1	Structural analysis	41
3.2.3.2	Molecular vibration interpretation	42
3.2.3.3	Surface area and pores studies	43
3.2.3.4	Morphological studies	43
3.2.3.5	Surface elemental analysis	44

3.2.3.6 Thermal analysis	44
3.3 Preparation of LDPE/rGO Nanocomposites	44
3.3.1 Structural studies	46
3.3.2 Phase transition behaviour and optical studies	46
3.3.3 Topological studies	46
3.3.4 Tensile measurement	47
3.3.5 Morphology observation	47
3.3.6 Oxygen transmission rate	48
3.3.7 Dielectric measurement	48
3.3.8 Gravimetric analysis	49
3.3.9 Thermal behaviour	50
3.3.10 TGA-MS analysis	52
3.3.11 Crystallinity characterization	53
3.3.12 Analysis on the photodegradation behaviour	53
<b>CHAPTER 4 : RESULTS &amp; DISCUSSION</b>	<b>55</b>
4.1 Introduction	55
4.1.1 Characterization on as-synthesized graphite oxide (GO) and reduced graphite oxide (rGO)	55
4.1.1.1 Mechanism of Graphite Oxide Formation	55
4.1.1.2 Structural analysis of graphite oxide and reduced graphite oxide	59
4.1.1.3 Bonding features	62
4.1.1.4 Surface area and pore size determination	63
4.1.1.5 Morphological study	64
4.1.1.6 Surface chemistry analysis	65
4.1.1.7 Thermal stability	67
4.1.2 Studies on the effect of rGO in LDPE	68
4.1.2.1 Structural analysis	68
4.1.2.2 Phase transition behaviour	69

4.1.2.3 Optical properties	70
4.1.2.4 Topological study	73
4.1.2.5 Transmission electron microscopy (TEM)	74
4.1.2.6 Tensile test	75
4.1.2.7 Morphological study on fracture surface	78
4.1.2.8 Gas barrier properties	79
4.1.2.9 Dielectric properties	81
4.1.2.10 Gravimetric analysis	82
4.1.2.11 Oxidation induction time (OIT)	84
4.1.3 Thermal degradation behavior of LDPE/rGO nanocomposites	87
4.1.3.1 Kinetics studies on thermal degradation of LDPE/rGO nanocomposites	87
4.1.3.2 Identification of thermal degradation products by coupled TGA-GC/MS	92
4.1.3.3 Differential scanning calorimetry (DSC)	96
4.1.4 Photo degradation behavior of LDPE/rGO nanocomposites	98
4.1.4.1 Optical properties	99
4.1.4.2 Structural analysis	101
4.1.4.3 FTIR spectra	102
4.1.4.4 Tensile test	106
4.1.4.5 Morphological study on fracture surface	110
<b>CHAPTER 5 : CONCLUSIONS and recommendations</b>	<b>113</b>
5.1 Conclusions	113
5.2 Recommendations	115
<b>REFERENCES</b>	<b>117</b>

©This item is protected by original copyright



## LIST OF TABLES

NO.		PAGE
Table 2.1:	Pro and con of various characteristics of GO based on different structural model (Wu et al., 2012).	20
Table 2.2:	Summary of methods in reducing graphene oxide and its potential application.	27
Table 4.1:	Calculated intensity ratio ( $I_D/I_G$ ) for graphite, graphite oxide (GO) and reduced graphite oxide (rGO).	62
Table 4.2:	OIT values obtained for LDPE and its nanocomposites with and without the effect of gravimetric analysis.	86
Table 4.3:	Thermal degradation behavior of LDPE/rGO nanocomposites at different heating rates.	90
Table 4.4:	Thermal degradation behaviour of LDPE/rGO nanocomposites at different heating rates.	96
Table 4.5:	Summary of thermal and crystallinity data.	98
Table 4.6:	Carbonyl index that calculated within the -C=O- range at 1750 – 1700 $\text{cm}^{-1}$ .	105
Table 4.7:	Vinyl index that calculated within the -CH <sub>2</sub> - range at 920 – 900 $\text{cm}^{-1}$ .	105

## LIST OF FIGURES

NO.		PAGE
Figure 2.1:	History of graphene oxide.	14
Figure 2.2:	Schematic of the recipe used by Brodie for graphene oxide preparation (Brodie, 1859).	15
Figure 2.3:	Schematic of the recipe used by Staudenmaier- Hofmann-Hamdi for graphene oxide preparation (Hummers Jr & Offeman, 1958).	16
Figure 2.4:	Schematic of the recipe used by Hummers for graphene oxide preparation (Hummers Jr & Offeman, 1958).	17
Figure 2.5:	Common idea purposed by researchers based on the functional group that appear on the graphene sheet.	18
Figure 2.6:	Schematic diagram of thermal annealing process for graphite oxide from temperature $\sim 180$ °C until $1000$ °C (Y. Zhu et al., 2010).	22
Figure 2.7:	Surface morphology of thermal reduced graphene oxide thin film at (a) $200$ °C and (b) $300$ °C (Tegou et al., 2016).	23
Figure 2.8:	Digital image of aqueous dispersion for (a) low concentration graphene oxide dispersion, (b) high concentration graphene oxide dispersion and (c) exfoliation of thermal reduced graphene oxide (Manivel et al., 2013).	24
Figure 2.9:	Microorganism reduction of graphene oxide to graphene.	27
Figure 2.10:	Overview of degradation of polymers (Vasile & Pascu, 2005).	33
Figure 2.11:	Steps of polymer biodegradation through microorganism.	34
Figure 2.12:	Radical generation for catalyst residues via UV radiation process.	36
Figure 3.1:	The experimental approach that applied in LDPE and its nanocomposites preparation.	45
Figure 4.1:	Plausible mechanism of synthesizing graphite oxide and reduced graphite oxide.	57
Figure 4.2:	Reduction mechanism of graphite oxide through sodium borohydride.	58
Figure 4.3:	The XRD patterns of graphite powder (G), graphite oxide (GO) and reduced graphite oxide (rGO).	60
Figure 4.4:	The Raman spectra for graphite, graphite oxide (GO) and reduced graphite oxide (rGO).	61

Figure 4.5:	Fourier transmission infrared spectra of as-synthesised GO and rGO.	63
Figure 4.6:	(a) The nitrogen gas adsorption and desorption isotherms and (b) pore size distribution of GO and rGO.	64
Figure 4.7:	Typical (a, b) SEM at magnification of x15 K and (c, d) TEM images at magnification of x 100 K for fully exfoliated graphene oxide (GO) and reduced graphite oxide (rGO) sheets. (a) and (c) are GO images and (b) and (d) are rGO images.	65
Figure 4.8:	The deconvolution of XPS C1s peak of (a) GO and (b) rGO. The insets are the full survey spectra of GO and rGO.	66
Figure 4.9:	The TGA (top) and DTG (bottom) curves for graphite oxide (GO) and reduced graphite oxide (rGO).	68
Figure 4.10:	Wide angle X-ray diffraction patterns of LDPE/rGO nanocomposites with various loaded amounts of 0.05 – 1 wt% of rGO.	69
Figure 4.11:	Phase transition of neat LDPE and its nanocomposites through Raman spectroscopy.	70
Figure 4.12:	(a) The optical property of neat LDPE and LDPE/rGO nanocomposites at 0.05 – 1 wt% rGO and (b) the linear relationship between A248/A293 ratio and loaded amounts of rGO.	72
Figure 4.13:	AFM micrographics in 2 dimensional for (a) LDPE and its nanocomposites at (b) 0.05 wt% rGO, (c) 0.3 wt% rGO and (c) 1.0 wt% rGO.	74
Figure 4.14:	TEM images for LDPE/rGO nanocomposites at (a) 0.05 wt%, (b) 0.3 wt% and (c) 1.0 wt% rGO content.	75
Figure 4.15:	(a) Stress strain curves, (b) tensile strength and (c) modulus of elasticity and elongation at break of LDPE/rGO nanocomposite from 0.05 to 1 wt%.	77
Figure 4.16:	FESEM images of (a) neat LDPE and LDPE/rGO nanocomposites at (b) 0.05, (c) 0.3 and (d) 1.0 wt% rGO for tensile fracture surface morphology at magnification x3K .	79
Figure 4.17:	The oxygen permeability of LDPE and LDPE/rGO nanocomposites as a function of added amounts of rGO ranging from 0.05 to 1 wt%.	80
Figure 4.18:	The (a) loss tangent and (b) dielectric constant of LDPE/rGO nanocomposites as a function of frequency.	82

Figure 4.19:	Gravimetric analysis of LDPE and its nanocomposites through hexane extraction.	84
Figure 4.20:	The thermal curves of oxidation induction time for LDPE and its nanocomposites	86
Figure 4.21:	The thermal curves of oxidation induction time for LDPE and its nanocomposites after the hexane extraction analysis.	87
Figure 4.22:	TGA curves of LDPE and its nanocomposites at different heating rates under nitrogen environment.	89
Figure 4.23:	Linearization plot for neat LDPE and LDPE nanocomposites obtained from K(a) and FWO(b) model.	91
Figure 4.24:	Plot of the activation energy ( $E_a$ ) versus rGO content calculated from the Kissinger model (K) and Flynn-Wall-Ozawa model (FWO).	91
Figure 4.25:	GCMS/TIC chromatograms for neat LDPE and LDPE nanocomposites at different TGA degradation temperatures of (a) 370°C, (b) 460°C, (c) 470°C, (d) 480°C and (e) 500°C.	93
Figure 4.26:	The proposed thermally scissoring mechanisms for (a) Neat LDPE and (b) LDPE/rGO nanocomposites under the thermal degradation process with possible molecular fragments.	95
Figure 4.27:	Non-isothermal crystallization DSC scans with a constant heating rate of 10 °C/min: (a) crystallization temperature, (b) melting temperature at nitrogen flow environment.	98
Figure 4.28:	Optical absorption spectra of photo irradiation LDPE and its nanocomposites according to the degradation time and rGO content, where (a) LDPE, (b) 0.05 wt% rGO, (c) 0.3 wt% rGO and (d) 1.0 wt% rGO.	100
Figure 4.29:	The structural behavior of LDPE and its nanocomposites according to the degradation time and rGO content, where (a) LDPE, (b) 0.05 wt% rGO, (c) 0.3 wt% rGO and (d) 1.0 wt% rGO.	102
Figure 4.30:	Norrish type II photo degradation mechanism of LDPE and its nanocomposites under UV B.	103
Figure 4.31:	FTIR spectra of LDPE and its nanocomposites according to the degradation time and rGO content, where (a) LDPE, (b) 0.05 wt% rGO, (c) 0.3 wt% rGO and (d) 1.0 wt% rGO. The insert figures are highlighted at the carbonyl region.	104
Figure 4.32:	Tensile strength of LDPE and its nanocomposites with different amount of rGO content ranging from 0.05 to 1 wt%.	107

Figure 4.33:	Elongation at break of LDPE and its nanocomposites with different amount of rGO content ranging from 0.05 to 1 wt%.	108
Figure 4.34:	Modulus of elasticity of LDPE and its nanocomposites with different amount of rGO content ranging from 0.05 to 1 wt%.	109
Figure 4.35:	Tensile fracture surface of LDPE and its nanocomposite (0.05, 0.3 and 1 wt%) at same magnification, 3K under different UV degradation time; where, (a) zero hour, (b) 120 hour, (c) 240 hour and (d) 360 hour.	111
Figure 4.36:	Tensile fracture surface of (a) LDPE, (b) 0.05 wt% rGO, (c) 0.3 wt% rGO and (d) 1.0 wt% rGO after 360 hours of UV radiation at same magnification, x 8K.	112

©This item is protected by original copyright

## LIST OF ABBREVIATIONS

AFM	Atomic force microscopy
ASTM	American standard testing method
BET	Brunauer-Emmett-Teller
BJH	Barrett-Joyner-Halenda
C <sub>2</sub> F	Graphite fluoride
CNT	Carbon nanotube
DA	Dodecyl amide
DI	Deionized
DMF	Dimethylformamide
DSC	Differential scanning calorimetric
EVA	Ethylene vinyl acetate
FDA	Food and drug administration
FESEM	Field emission scanning electron microscopy
FTIR	Fourier transmission infrared spectroscopy
FWO	Flynn-Wall-Ozawa
GC	Gas chromatography
GO	Graphene oxide
H <sub>2</sub> O <sub>2</sub>	Hydrogen peroxide
H <sub>2</sub> SO <sub>4</sub>	Sulfuric acid
HDPE	High density polyethylene
HMWHDPE	High molecular weight high density polyethylene
HNO <sub>3</sub>	Nitric acid
IR	Infrared
K	Kissinger
KBr	Potassium bromide
KClO <sub>3</sub>	Potassium chlorate
KMnO <sub>4</sub>	Potassium permanganate
LDPE	Low density polyethylene
LLDPE	Linear low-density polyethylene
MS	Mass spectroscopy
MSD	Mass selective detector

MWNT	Multi-walled nanotubes
MWS	Maxwell-Wagner-Sillars
NaBH <sub>4</sub>	Sodium borohydride
NaNO <sub>3</sub>	Sodium nitrate
NMR	Nuclear magnetic resonance
OIT	Oxidative induction time
OTR	Oxygen transmission rate
PB-1	Polybutene-1
PC	Polycarbonate
PE	Polyethylene
PMMA	Poly(methyl methacrylate)
PMP	Polymethylpentene
PP	Polypropylene
PPC	Poly(propylene carbonate)
PPMS	Physical property measurement system
PS	Polystyrene
rGO	Reduced graphite oxide
SEM	Scanning electron microscopy
TEM	Transmission electron microscopy
TGA	Thermogravimetric analysis
THF	Tetrahydrofuran
UHMWPE	Ultra high molecular weight polyethylene
UV	Ultraviolet
ULDPE	Very low density polyethylene
XPS	X-ray photoelectron spectroscopy
XRD	X-ray diffractometer

## LIST OF SYMBOLS

$\lambda$	Wavelength
$d$	d-spacing
$\theta$	Angle
$n$	Integral
$\Delta c$	Difference in gas concentration
$l$	Length
$J$	Diffusion flux
$D$	Diffusivity
$C_p$	Parallel capacitance
$\epsilon_0$	Permittivity of free space
$\epsilon_r$	Relative dielectric constant
$t$	Thickness
$W_b$	Weight of the initial thin film
$W_a$	Weight of the thin film after extraction
$k$	Rate constant
$A$	Pre-exponential factor
$E_a$	Activation energy
$R$	Universal gas constant
$T$	Thermodynamic temperature
$\beta$	Heating rate
$\Delta H_f$	Enthalpy of melting
$\Delta H_c$	Enthalpy of crystallization
$\Delta H_{f100\%}$	Enthalpy of the melting for fully crystalline material



## LIST OF EQUATIONS

NO.		PAGE
3.1	$n\lambda = 2d\sin\theta$	43
3.2	$J = -D \cdot \left(\frac{\Delta c}{l}\right)$	49
3.3	$C_p = \frac{A\varepsilon_0\varepsilon_r}{t}$	50
3.4	$\text{hexane extractables, \%} = \frac{(W_b - W_a) \times 100 \times 0.935}{W_b}$	50
3.5	$k = Ae^{\frac{-E_a}{RT}}$	51
3.6	$\ln \frac{\beta}{T_p^2} = -\frac{E_a}{RT}$	52
3.7	$\frac{d(\ln \frac{\beta}{T_p^2})}{d(\frac{1}{T})} = -\frac{E_a}{R}$	52
3.8	$\ln \beta = K - 1.052 \frac{E_a}{RT}$	52
3.9	$\frac{d(\ln \beta)}{d(\frac{1}{T})} = -1.052 \frac{E_a}{RT}$	52
3.10	$\text{Degree of crystallinity} = \frac{\Delta H_f - \Delta H_c}{\Delta H_{f100\%}} \times 100\%$	54
4.1	$\text{KMNO}_4 + 3\text{H}_2\text{SO}_4 \rightarrow \text{K}^+ + \text{MNO}_3^+ + \text{H}_3\text{O}^+ + 3\text{HSO}$	57
4.2	$\text{MNO}_3^+ + \text{MNO}_4^- \rightarrow \text{MN}_2\text{O}_7$	57
4.3	$2\text{NANO}_3 + \text{H}_2\text{SO}_4 \rightarrow 2\text{HNO}_3 + \text{NA}_2\text{SO}_4$	57

# SINTESIS, PENCIRIAN DAN SIFAT-SIFAT KOMPOSIT NANO POLIETILENA BERKETUMPATAN RENDAH TERISI GRAFIT TERKURANG

## ABSTRAK

Bahan berasaskan grafit telah menjadi calon yang menjanjikan dalam nanokomposit poliolefin dalam aplikasi luas seperti bahan pembungkusan. Walau bagaimanapun, penggunaan gabungan ini menimbulkan keraguan tentang kesan haba yang digunakan pada nanokomposit. Di sini, kajian sistematik telah dijalankan untuk menyiasat kesan penurunan oksida grafit (rGO) ke arah bahan poliolefin. Kaedah pengecoran hijau dan mudah diperkenalkan dalam fabrikasi polietilena berketumpatan rendah / pengurangan grafit oksida (LDPE / rGO) nanokomposit dengan kandungan pengisi 0.05 - 1 wt%. Tanpa sebarang pengubahsuaian antara polietilena dan oksida grafit yang diturun, beberapa pencirian telah dilaksanakan ke arah nanokomposit. Sifat optik melalui spektroskopi yang kelihatan UV secara berkesan mengenal pasti ketelusan nanokomposit, di mana ketelusan berkurangan dengan penambahan rGO. Ujian ketegangan juga dilakukan untuk menentukan sifat ketegangan filem yang direka. Filem yang berketumpatan 0.3 wt% rGO menunjukkan kekuatan ketegangan tertinggi secara keseluruhan. Halangan gas bersama-sama dengan sifat-sifat dielektrik dari nanokomposit dikaji secara mendalam. Mikroskop elektron penghantaran (TEM) digunakan untuk memerhatikan penyebaran dan morfologi grafit oksida yang dikurangkan dalam polietilena. Selanjutnya, penguraian haba nanocomposites diselidiki melalui analisis termogravimetrik (TGA). Kajian kinetik terhadap nanokomposit yang berdegradasi telah menunjukkan bahawa model Flynn-Wall-Ozawa (FWO) adalah satu langkah lebih tinggi berbanding dengan model Kissinger (K). Walaupun hanya terdapat satu langkah kemerosotan terma yang muncul namun unsur-unsur yang terurai masih tidak diketahui. Oleh itu, kromatografi gas (GC) dan spektroskopi jisim (MS) ditambah dengan TGA digunakan untuk memisahkan sebatian yang berkembang ke dalam alkana, alkena dan kumpulan aromatik masing-masing. Gas yang beracun hanya akan dikeluarkan apabila nanokomposit dipanaskan hingga 460 °C. Dengan penambahan rGO dalam matrik LDPE, tingkah laku degradasi nanocomposites mengenal pasti melalui sinaran UV. Terdapat hanya sedikit atau tidak ada perbezaan pada sifat-sifat filem nipis selepas 360 jam radiasi UV-B. Berdasarkan analisis, kajian menunjukkan bahawa penambahan rGO ke atas LDPE akan meningkatkan sifat optik, mekanik, termal dan dielektrik. Ini telah meluaskan aplikasi LDPE/rGO yang berpotensi berfungsi sebagai bahan pembungkus.

# **SYNTHESIS, CHARACTERIZATION AND PROPERTIES OF LOW DENSITY POLYETHYLENE FILLED WITH REDUCED GRAPHITE OXIDE**

## **ABSTRACT**

Graphite based materials have become promising candidates in polyolefin nanocomposites in widening the application such as a packaging material. However, the utilization of these combination exhibits a doubt on how was the effect once heat is applied onto the nanocomposites. Herein, a systematic study has been carried out to investigate the effect of reduced graphite oxide (rGO) towards low density polyethylene (LDPE). A simple solvent casting method was carried out in fabricating low density polyethylene / reduced graphite oxide (LDPE/rGO) nanocomposites with the filler contents of 0.05 – 1 wt%. Without any modification between LDPE and rGO, several characterizations have been implemented towards the nanocomposites. Optical properties through UV-visible spectroscopy were effectively identifying the transparency of the nanocomposites, where the transparency decreased with the increased of rGO. The tensile test was also carried out in order to determine the tensile properties of the fabricated film. Thin film with 0.3 wt% of rGO content has showed highest tensile strength compared to the rest of the nanocomposites film. Gas barrier together with the dielectrical properties of the nanocomposites were studied in depth. Transmission electron microscopy (TEM) was employed to observe the dispersion and morphology of the rGO in LDPE. Further, thermal decomposition of the nanocomposites was investigated through thermogravimetric analysis (TGA). Kinetic studies on the degradation nanocomposites had concluded that Flynn-Wall-Ozawa (FWO) model is one step higher compared to Kissinger (K) model. In order to identify the elements that decomposed, gas chromatography (GC) and mass spectroscopy (MS) coupled with TGA were used to separate the evolved compounds into alkane, alkene and aromatic groups, respectively. Where, toxic gaseous will only being released out when the nanocomposites was heated up to 460 °C. With the addition of rGO in the LDPE matrix, the degradation behaviour of the nanocomposites was identifying through UV radiation. There is only slight difference on the thin film's properties after 360 hours of UV-B radiation. Based on the analysis, the studies clearly indicated that the feasibility of incorporating rGO into the LDPE matrix had improved the optical, mechanical, thermal and dielectric properties. This has widened the application of LDPE/rGO nanocomposites in serving as a packaging material.

## CHAPTER 1 : INTRODUCTION

### 1.1 Nanocomposites: Current Status, Challenges and Future

Nanocomposites briefly defined as nanofillers bonded to a matrix, which have been reported since past decades has increased an interested for commercial use. Fillers play an important role in modifying the desirable properties in composites and can adversely affect some properties of the neat matrix with the main aim to reduce the cost of the composites. In conventional composites, fillers are usually added into matrix as reinforcement to rebuild the properties of the composites. The most widely employed composites nowadays in industrial sectors are those with micron-sized particles or fibers as reinforcement. In fact, traditional micro composites might have achieved the optimizing properties in terms of physical and mechanical properties (Pezzin, Amico, Coelho, & de Andrade, 2011). Therefore, about twenty years ago, researchers proved that novel materials could be produced with tailored properties using nanofillers. Current trend of fillers used is available on nanoparticles, nanoplatelets, nanofibers, carbon nanotubes, and more recently on graphite (Pezzin et al., 2011).

Substitution of the traditional micro-reinforced materials using polymer nanocomposites has attracted most of the researchers nowadays. Indeed, the combination of nanomaterials with thermoplastic or thermoset polymers lead to very interesting mechanical or physical properties. According to Mohammed (2016) different particle size of titanium dioxide has been implemented into thermoset materials such as epoxy with the purpose to study its physical properties. Wear rate and

hardness test on the polymer nanocomposite has showed better properties compared to composites filled with micron size filler. Besides, comparison has been made between nano and sub-micrometer zinc oxide with an organophilic surface layer as fillers in poly(methyl methacrylate) based on its UV absorber and thermal stabilizer. Nano sized zinc oxide showed effective UV absorber than submicrometer zinc oxide. Therefore, Anžlovar, Crnjak Orel, and Žigon (2008) concluded that the average particle size is an important parameter for optimizing the composites properties.

Although nanotechnology is now revolutionizing the world of materials and has very high impact in developing a new generation of composites with enhanced functionality and wide range of applications. But investment in state of the equipment and the enlargement of core research team's is another bottleneck to bring out innovative technologies on nanocomposites. A part of that, nano fillers selection based on the requirement needed such as an interfacial interaction or compatibility with the polymer matrix and the processing technique which aimed for the proper uniform dispersion and distribution of nano-particles or nano-particles aggregates within the polymer matrix is another problem should be considered too (Müller et al., 2017) .

Thus, extension of this nanotechnology using additional types of polymer system would likely to be a prerequisite aim as the future trends for nanocomposites materials. New compatibility strategies between nano fillers and polymer matrix are also one of the interests in the development of properties enhancement for polymer nanocomposites.

## 1.2 Graphite Oxide based Thermoplastic Nanocomposites

Graphite oxide based fillers in polymer nanocomposites has hold potential for various application. Thermoplastic polymer as matrix with graphite based filler include polypropylene (PP), polymethylpentene (PMP), polybutene-1 (PB-1), polystyrene (PS), poly(methyl methacrylate) (PMMA) and polycarbonate (PC) (Ma, Siddiqui, Marom, & Kim, 2010). To achieve large property of enhancements in polymer nanocomposites, it is important to focus on the preparation method. Layered structure graphite oxide must be exfoliated and well dispersed in the polymer matrix. Upon achieving this criterion, ultrasonication have been wisely use extensively to produce highly exfoliated nanoplatelets for nanocomposites. However, it is proved that graphite oxide can be easily dissolved in a variety of solvent such as dimethylformamide (DMF) and tetrahydrofuran (THF), which will further help to improve interfacial interaction with polymer matrix.

Studies on poly(propylene carbonate) (PPC) reinforced graphite oxide was reported by J. Gao et al. (2011) using solvent mixing method during preparation. As expected, the mechanical properties of PPC/GO nanocomposites have been highly improved together with tensile strength and Young's modulus by adding of only 1wt% graphene oxide. These properties are comparable to those of polyethylene and poly (L-lactic) acid as matrix (Chaudhry & Mittal, 2013; Pinto, Cabral, Tanaka, Mendes, & Magalhães, 2013). Other than that, Kuila et al. (2012) claims that linear low density polyethylene filled modified graphene oxide using dodecyl amide (DA) with the purpose to achieve better dispersion in the polymer matrix due to the nucleophilic addition of organic molecules to the surface of graphene is an effective way to the bulk

production of surface modified graphene (Bourlinos et al., 2003; Stankovich et al., 2010) were also made some improvement in the storage moduli and thermal stability than the neat LLDPE. In addition, graphene and silica hybrid fillers to PP-based nanocomposites has increased the tensile strength by 13.8% when the filler content was fixed at 0.25 wt% (Kamal, Khan, Haider, Alghamdi, & Asiri, 2017). A previous study used octadecylamine-modified graphene oxide into PP and found that the layered morphology exhibited better thermal stability and mechanical properties compared to the neat PP (H. X. Zhang et al., 2017). However, the incorporation of carbonaceous materials into LDPE has received less attention. Bu, Huang, Li, and Jiang (2016) have filled the antioxidant functionalized reduced graphene oxide (rGO) to LDPE and found that functionalized rGO could enhance the dielectric constant as well as improve the dielectric loss tangent of nanocomposites. An improvement in the thermal behavior of the composites was noticeable when 3 wt% functionalized graphene filler content was loaded to the linear LDPE matrix (Kuila et al., 2011). However, the physicochemical properties of incorporation of rGO into the LDPE matrix with respect to the packing materials including optical, tensile, thermal and dielectrical properties are yet to be well understood. In addition, the surface modification of fillers shoots up the cost of nanocomposites and longer time is needed during fabrication process, which may hamper the industrial adaption (Tanahashi, 2010).

With these, studies on graphite oxide based thermoplastic are piling up highly desirable demand to develop novel LDPE/rGO nanocomposites without any surface modification for multifaceted applications.

### 1.3 Problem Statement

The current trend of packaging materials use biopolymer as matrix in packaging application has become potentially renewable alternative to petroleum-based plastics due to the long term benefits of reducing global warming pollution and the dependence on fossil fuels. Although bio-based polymer matrix sounds "green" but according to the Life Cycle Analysis of biopolymer, bioplastic has resulted in more pollution or energy consumption imposing higher costs to the society than the conventional petroleum based polymer matrix. Bioplastic that designed to be composted, not recycle has become one of the issues that concern nowadays (S. Lee & Xu, 2005).

Among the list of the polyolefin materials that is being used in the packaging application such as high density polyethylene (HDPE), linear low density polyethylene (LLDPE) and low density polyethylene (LDPE), the LDPE is chosen as the polymer matrix for packaging application. By comparing the characteristics between these polyolefin materials, low density polyethylene (LDPE) with its unique properties such as having the most excessive branching in its structural has provided a good flow properties that can make it particularly for plastic film applications, high ductility, good chemical resistance and excellent water resistance has also become the reason why LDPE is the most outstanding characteristics among the polyolefin materials (Fayyaz, Muhamad, & Sulong, 2018). Unfortunately, LDPE is poor in both gas barrier and less tensile strength. In order to overcome the above mentioned drawback, incorporating layered structure graphite oxide into the LDPE matrix, which served as packaging material was studied.



To overwhelm gas barrier of the selected polymer matrix, two dimensional carbon based filler was selected as it contains unique characteristics. Besides, sheets structure filler was highly introduced in the nanocomposites system. Although there are various types of two dimensional carbon based materials, such as graphene, graphene oxide, graphite oxide, etc. And, graphene oxide can be exfoliating well if the polymer matrix used is hydrophilic in nature. But, along with the study, hydrophobic polyethylene which has totally opposite nature with graphene oxide is being selected as the matrix used. Thus, reduction process was applied onto the graphene oxide so that reduced graphite oxide can be used as the filler in the nanocomposites. Although there are numbers of researchers have been studying on the characteristics between carbon based filler and polymer matrix, yet limited amount towards the unmodified filler filled polymer matrix and its degradation behaviour of the composites materials is still remain unknown.

Aside from examine the effect of reduced graphite oxide that incorporated into LDPE matrix that focus as packaging material, the degradation behaviour of the nanocomposites was taken into account in order to obtain a reliable material in packaging application. With these, two different degradation aspects were observed from thermal and ultraviolet light at wavelength 305 nm.

#### **1.4 Objectives of study**

The aim of this work focuses on preparation and characterization of graphite oxide nanoplatelet as filler that incorporate into the low density polyethylene thin film nanocomposite. Emphasis is given on the synthesis of the graphite oxide and reduced